

1

Research Frontiers in Solar Light Harvesting

Srabanti Ghosh

CSIR – Central Glass and Ceramic Research Institute, Fuel Cell and Battery Division, 196, Raja S.C. Mullick Road, Kolkata 700032, India

1.1 Introduction

In continuously growing technology-driven society, an urgent need for efficient solar light harvesting to achieve sustainable solutions in science and industry exists [1, 2]. The rapid growth of industries and some unavoidable human activities cause environment pollution to be a threat to the society. Solar-energy-mediated advanced oxidation process in water purification is a highly desirable approach [3]. To use the solar light, energy harvested from the sun needs to be efficiently converted into chemical fuel that can be stored, transported, and used upon demand. Over the last few decades, a significant effort has been made to develop active materials including inorganic, organic, ceramic, polymeric, and carbonaceous, their composites with tunable size and structures [4–6]. A broad range of materials including metal oxides, chalcogenides, carbides, nitrides, and phosphides of various compositions such as heterogeneous, plasmonic, conjugated polymers, porous carbon-based materials, and graphene-based materials has been explored to address/solve energy and environment-related research challenges [7–10]. In this context, oxide-based semiconductors, in particular, TiO_2 , have been recognized as efficient and widely explored photocatalysts. Semiconductor-oxide-based catalysts is essentially limited by low quantum yield which results from the fast charge carrier (e^-/h^+) recombination, and the necessity to use UV irradiation (5% of total sun energy) having wide bandgap [11, 12]. To overcome these limitations, surface-tuning strategies and modification of oxides on the nanometer scale have been developed via doping or surface modifications to produce visible-light-responsive photocatalysts. Indeed, TiO_2 doped with N, C, or S or its modification with metal nanoparticles (Ag, Au, Pt, Cu, Bi) has extended its activity toward the visible region [13–16]. However, the photocatalytic activity of the modified materials in the visible light is still not sufficient for commercial applications. Research efforts are therefore increasingly being carried out to design and develop more efficient novel visible-light active catalysts for photocatalysis and solar energy conversion. A considerable number of novel synthetic strategies including

fabrication of plasmonic-based novel catalysts, heterojunctions, and cocatalyst have been proposed to offer new visible-light-active photocatalytic materials as potential substitutes of TiO_2 for the most relevant photocatalytic applications such as detoxification and disinfection, removal of inorganic pollutants, water splitting, and organic synthesis [17–19]. In this regard, the loading of cocatalysts or secondary semiconductors, which can act as either electron or hole acceptors for improved charge separation, is a promising strategy for enhanced catalytic activity. A more innovative implementation of this idea would be based on the use of polymer-based composites, which could allow enhanced charge separation with respect to the photocatalytic activity of the inorganic component alone. In this chapter, the state of the art on development of novel nanostructures and the concept of heterojunction for efficient visible-light-driven water splitting, organic or inorganic pollutant degradation, and organic transformation have been discussed. The structural features of various nanostructured catalysts and their correlation are explained in detail. An overview of recent research efforts in the applications of visible-light-active photocatalysts, which include semiconductor metal oxides (TiO_2 , Fe_2O_3 , Cu_2O , etc.), polymeric graphitic carbon nitride (C_3N_4), plasmonic nanostructures (Au, Ag, etc.), conducting polymers nanostructure (PEDOT, PANI, PDPB, etc.), heterostructures, and other novel materials in degradation of photocatalytic pollutants, hydrogen generation, CO_2 reduction, and selective redox organic synthesis are summarized.

1.2 Visible-Light-Driven Photocatalysis for Environmental Protection

Environmental pollution issues prompted the finding of potential solutions to clean up water and environmental detoxification via exploring clean energy routes through solar-light-induced photocatalysis. Extensive research has been done in the area of photocatalytic removal of organic, inorganic, and microbial pollutants using semiconductor photocatalysts (e.g., TiO_2 , ZnO, and CdS) for wastewater purification [20–23]. The key to the success of solar energy conversion is the development of high-performance materials of well-matched photo absorption with solar spectrum (visible-light-harvesting capability), efficient photoexcited charge separation to prevent electron–hole recombination, and adequate energy of charges that carry out the photodegradation of dye and other toxic molecules. Continuous efforts have been made to generate active photocatalysts under visible light, but their efficiency is low due to fast charge recombination [24]. Many excellent reviews have also come up regarding the development of oxide-based semiconductors, in particular, TiO_2 , via fine-tune of several electronic characteristics (e.g., atomic configuration, bandgap energy, band position, and lifetime of electrons and holes) [25–27]. In addition to dye sensitization, doping with metals and nonmetals, formation of heterojunctions have been extensively used to enhance the visible-light response of TiO_2 materials and discussed in detail in Chapters 2, 5, 6, 11, and 16. For example, TiO_2 doped with N, C, F, or S or its modification with metal nanoparticles has

extended its activity toward the visible region [15, 28–30]. Visible-light activities arise from the changes of bandgap structure of semiconductor via adsorbed modifiers (surface modification) or bandgap narrowing (doping). Synthesis of different materials, such as M/TiO_2 ($M=\text{Cu, Ag, Au, Pt, Pd, Bi, Ag—Au, Ag—Cu, Au—Cu, Ag—Pt}$), and the effect of metal modification on the photocatalytic activity have been discussed in Chapter 6. Moreover, Chen *et al.* reported disordered TiO_2 nanophase derived from hydroxylation through hydrogenation treatment, which marked as black TiO_2 and a considerable enhancement in visible-light-induced photocatalytic activity [31]. It has been reported that hydrogenation treatment induced the oxygen vacancies and Ti^{3+} sites in black TiO_2 , resulting in the bandgap narrowing and the separation of photogenerated electrons and holes, which enhanced solar absorption and significantly improved the photocatalytic activity of TiO_2 [32, 33]. A variety of synthetic strategies of black TiO_2 are outlined, and the structural and chemical features, electronic properties, and catalytic activity of the black TiO_2 nanomaterials are described in Chapter 5. Furthermore, oxygen-rich layered titanium oxide is also useful for enhanced visible-light photoactivity [34, 35]. Kong *et al.* reported Ti—O—O coordination bond in layered titanium oxide (composed of TiO_6 layers, and interstitial hydrated H^+ ions) initiated visible-light-driven photocatalytic activity [36]. Presence of Ti—O—O coordination bonds lowers the bandgap and promotes the charge separation of the photoinduced electron–hole pairs.

Another important example is combination of nanostructured plasmonic metals with a oxide-based semiconductor, which significantly enhanced the photocatalytic activity due to the local surface plasmon resonance (LSPR) effect with very large absorption and scattering cross sections [28, 29]. In fact, LSPR causes an optical antenna effect, which efficiently harvests light and localizes electromagnetic waves at the nanoscale, and the charge carrier formation with efficient separation is obtained at the semiconductor/liquid interface, which benefits the photocatalytic reactions [37–40]. A series of reactions have been tested on Ag, Au, and Cu surfaces, illustrating that low-intensity visible-photon illumination can significantly enhance the rates of chemical transformations as well as control reaction selectivity with different mechanisms as discussed in Chapter 6. Direct plasmonic photocatalysis is believed to occur through the transient transfer of energetic electrons to adsorbate orbitals and the nature of the adsorbate may have a significant impact to control selectivity in plasmon-driven reactions [17]. These heterogeneous oxide-based semiconductor photocatalysts have been also explored for the removal of inorganic wastewater pollutants including cyanide-containing waste and heavy metal pollutants, such as arsenic species and hexavalent chromium [41–43]. Notably, due to high toxicity and carcinogenicity of hexavalent chromium (Cr(VI)), the concentration of Cr(VI) in wastewater should be controlled in acceptable levels before its release in order to protect potable water supplies [44, 45]. Although, molecular CO_2 has a very low electron affinity and is chemically inert as well as very stable, photogenerated energetic electrons from photocatalysts can reduce CO_2 to methane (CH_4) and carbon monoxide (CO). The photocatalytic reduction of CO_2 using solar energy has drawn considerable attention, which mimics the biological photosynthesis in plants [46–48]. It combines the reductive half reaction of CO_2 fixation with

a well-matched oxidative half reaction of water oxidation, in order to achieve a carbon neutral cycle, which accomplished with the environment protection. Over the last few decades, various semiconductor photocatalysts, including metal oxide, sulfide, and oxynitride, have been investigated [49, 50]. However, the overall efficiency of the CO₂ photocatalytic reduction has been limited by the purification and separation of products. Consequently, efficient and selective production of highly valuable fuel compounds is a vital issue for practical CO₂ photoreduction systems. Despite of huge attempts to enhance visible-light activity by narrowing the bandgap of TiO₂ through doping, large-scale application is limited due to defect-induced charge trapping and recombination sites of photoexcited charge carriers. In this regard, plasmon-based photocatalysts have demonstrated significantly higher photocatalytic performance in comparison to other known visible-light photocatalysts (e.g., N-doped TiO₂); however, the poor photostability of silver salts reduced the photoactivity of the doped TiO₂ material, which limits its extensive use as a visible-light photocatalyst [15, 51–53]. Hence, a dopant-free, pure catalyst with a bandgap that matches the visible-light energy would be ideal. Numerous efforts have been made for the development of new visible-light-induced photocatalysts, and some oxides have shown visible-light-driven catalytic activity, such as InVO₄, BiVO₄, Bi₂MoO₆, WO₃, and Bi₂WO₆. Recently, visible-light-responsive photocatalytic activity of conjugated polymer nanostructures (CPNs) such as poly(diphenylbutadiyne) (PDPB) nanofibers, poly(3,4-ethylene dioxythiophene) (PEDOT) nanospindle, and poly(3-hexyl thiophene) (P3HT) nanospheres have been reported for degradation of organic pollutants [54–56]. These CPNs demonstrated high photocatalytic activity under visible light without the aid of sacrificial reagents or precious metal cocatalysts. These novel photocatalytic materials have been proposed as potential substitutes of TiO₂ for the most relevant photocatalytic applications, such as detoxification and disinfection, water splitting, and organic synthesis.

Compared to individual semiconductor photocatalysts, composites of two or more semiconductor systems, that is, heterostructures, are advantageous in terms of more efficiently facilitating charge separation and charge carrier transfer, thereby substantially improving photocatalytic efficiency. A very large number of different semiconductor combinations have been investigated, such as metal/semiconductor, carbon group materials/semiconductor heterostructures, semiconductor/semiconductor heterostructures with different models including type I and type II heterojunctions, p–n heterojunctions, and Z-scheme [57–61]. Chapter 8 summarizes the recent strategies to develop such heterostructures and highlights the most recent developments in the field. For charge carrier separation, TiO₂ has been commonly used to form heterostructures with CdS [62, 63], CdSe [64], CuO [65], AgBr [66], PbS [67] for enhanced photocatalytic activities, such as degradation of organic molecules, H₂ generation, and CO₂ reduction. For example, the integration of a potential semiconductor nanocrystal, ZnO, with a narrow band-gap conducting polymer has also shown to be an effective means of promoting charge carrier separation and improving the utilization of solar light [68]. A deep understanding of the charge transfer process through fundamental studies toward the rational design of heterostructures exhibiting high visible-light-harvesting efficiency is addressed in Chapter 9. Similarly, the

use of multiple inorganic domains within these heterostructures enables a rapid dissociation of excitons into a spatially separated pair of charges that bears a minimal probability of the backward recombination, with a high extinction coefficient in the visible range and a low exciton binding energy, which is beneficial to photocatalytic applications [69]. In addition to metal oxides, metal sulfides or chalcogenides have been employed for photocatalytic applications [70]. Ganguli *et al.* reported a type II semiconductor, ZnO/CuS heterostructure, to increase the absorbance in the visible-light region and successful charge separation from CuS to ZnO through the hexagonal nanotubes (NTs) of ZnO, leading to enhanced visible-light-induced photocatalysis for the degradation of organic pollutants due to the efficient separation of photoinduced carriers [71]. Wang *et al.* synthesized mesoporous yolk-shell $\text{SnS}_2\text{-TiO}_2$ and applied them for the visible-light-driven photocatalytic reduction of Cr(VI) [72].

The two-dimensional (2-D) structure of graphene possessing the large surface area can accommodate semiconductor nanoparticles, and the injection of photoexcited electrons from the semiconductor particle can readily be transported along the graphene surface due to its superior electronic conductivity and high mobility of charge carriers [73–76]. Hence, graphene is a promising component to create efficient composite photocatalysts for dye degradation, organic transformations, and reduction of carbon dioxide (CO_2) [77, 78]. For example, Liang *et al.* prepared less defective graphene-P25 nanocomposites for the photocatalytic CO_2 reduction under visible light [79]. Yu *et al.* synthesized CdS nanorod/r-GO heterostructures, which demonstrated high catalytic activity for the CO_2 reduction with 10 times higher CH_4 production rate compared to pure CdS and even better than Pt loaded CdS [80]. Moreover, Meng *et al.* established the concept of photogenerated electron transfer from $\alpha\text{-Fe}_2\text{O}_3$ nanoparticles to the graphene surface through transient absorption spectroscopy and time-domain terahertz spectroscopy, which increases the lifetime of charge carriers and, consequently, improve the photocatalytic activity [81]. Li *et al.* showed bandgap engineering and enhanced interface coupling of graphene-BiFeO₃ nanocomposites by the formation of Fe—O—C bonds, which demonstrated enhanced photocatalytic activity under visible-light illumination [82]. Yang *et al.* synthesized functionalized graphene sheets/ZnO nanocomposites that exhibited an enhanced photocatalytic activity for the degradation of rhodamine [83]. Zhang *et al.* showed the excellent performance of CdS-graphene nanocomposite photocatalyst for selective oxidation of alcohol to corresponding aldehyde [84]. Moreover, Han *et al.* successfully prepared ternary CdS/ZnO/graphene composite, which showed enhanced visible-light-induced photocatalytic activity in comparison to binary composites and pure ZnO and CdS [85]. Hence, this study highlights the significance of charge transport on graphene surface of heterostructures during catalysis reaction. Recently, another graphene-like material, layered structures of MoS_2 have been used as a cocatalyst to modify different semiconductors for hydrogen production and pollutant removal [86–88]. Zhou *et al.* prepared few-layered MoS_2 nanosheet-coated TiO_2 nanobelt heterostructures to increase the visible-light absorption ability of TiO_2 , and $\text{MoS}_2/\text{TiO}_2$ composites showed high photocatalytic activity in the degradation of organic dyes [89]. Another example, few-layered $\text{MoS}_2/\text{BiOBr}$ hollow microspheres demonstrated superior

visible-light-response photocatalytic activity for ciprofloxacin and rhodamine B removal in comparison to BiOBr alone [90]. The conduction band (CB) edge potential of MoS₂ (−0.09 eV) is more negative than that of BiOBr (0.29 eV), and the valence band (VB) of BiOBr (3.06 eV) is more positive than that of MoS₂ (1.81 eV). The energy difference between the CB edge potentials of MoS₂ and BiOBr leads to the transfer of the electrons from the CB of MoS₂ to that of BiOBr. Hence, the photogenerated electrons can be collected by BiOBr, and holes can be collected by MoS₂, which causes effective charge separation and can be reflected in enhanced photocatalytic activity. Graphitic carbon nitride (g-C₃N₄) considered as a low-cost photocatalytic system having a graphene-like structure consisting of two-dimensional frameworks of tri-*s*-triazine connected via tertiary amines with a bandgap of ~2.7 eV, corresponding to an optical wavelength of 460 nm in the visible-light range [91, 92]. Hence, two-dimensional g-C₃N₄ nanosheets having a graphene-like structure consisting of two-dimensional frameworks of tri-*s*-triazine connected via tertiary amines also offers large surface area and active sites, which are beneficial for photocatalytic oxygen evolution and CO₂ photoreduction [93, 94]. Moreover, transition-metal-based inorganic compounds have also been coupled with g-C₃N₄ for the fabrication of noble-metal-free heterostructured photocatalysts. The composites of g-C₃N₄ and metal oxides (e.g., TiO₂, ZnO, In₂O₃, and Bi₂WO₆) have been investigated by various research groups for CO₂ photoreduction [95–98]. Chapter 15 covers the current progress of visible-light-induced conversion of CO₂ to fuels by heterogeneous photocatalysts over the metal oxides, sulfides, phosphides, oxynitrides, and organic semiconductors as well as highlights the importance of graphitic carbon nitrides as emerging photocatalyst.

Another way to extend the range of TiO₂ activity to the visible region is modification with visible-light-absorbing dyes such as rose bengal, chlorophyllin, porphyrins, or phthalocyanines [99–101]. Dye-modified TiO₂ can be used for visible-light-assisted photocatalytic degradation of a great variety of organic pollutants from wastewater effluents either by oxidative or reductive processes. Sensitization of TiO₂ and other photocatalysts by modification with dyes has been reviewed in Chapter 10, with an emphasis on the physicochemical properties of the modified photocatalysts, the mechanisms involved in the transformation of pollutants, and the possible technological applications. However, the use of organic dyes as sensitizers of semiconductors has the disadvantage of gradual degradation of organic molecules, which in turn affects the stability of catalysts.

1.3 Photocatalysis for Water Splitting

Solar H₂ production by photocatalytic water splitting appears to be an attractive route to store solar energy in chemical bonds from renewable resources (water and sunlight) [102, 103]. However, the complexity of resolving the complete water splitting problem, structure–property relationships of photocatalysts for the two half reactions of water splitting, hydrogen and oxygen evolution reactions in the

presence of sacrificial reagents have been studied extensively [104, 105]. Hence, light-driven water splitting is recognized as one of the major scientific challenges for hydrogen production. Since the first pioneer report of photocatalytic water splitting using titanium dioxide by Fujishima and Honda, numerous research studies have been conducted on semiconductor materials with proposed mechanisms of photocatalytic water splitting [47]. A photocatalytic system for the photoreduction of protons to produce H_2 consists of a photosensitizer, a catalyst, and sources of protons and electrons [104]. The reaction is first initiated by photon absorption, which generates numerous electron–hole pairs with sufficient potentials. The relevant photoreduction processes involve

- i) absorption of light by the photosensitizer and subsequent internal charge separation
- ii) intermolecular charge transfer (i.e., reduction of the catalyst by the photosensitizer and reduction of the photosensitizer by direct hole donation from a sacrificial electron donor)
- iii) catalytic formation of H_2 by the reduced catalyst.

Sacrificial electron acceptors ($S_2O_8^{2-}$, $Ce(SO_4)_2$, $FeCl_3$, Ag^+ from $AgNO_3$, etc.) and donors (ethanol, methanol, triethanolamine, Na_2S , $Na_2S_2O_3$, and Na_2SO_3) control the production of either hydrogen (electron donor) or oxygen (electron acceptor) by combining with the respective charge carrier. The fundamental aspects of direct photoelectrochemical (PEC) water splitting at semiconductor electrodes are discussed along with recent experimental progresses in Chapter 3. The roles of different experimental parameters for successful water-splitting systems are also included. An overview of recent research progress in photochemically induced water splitting into hydrogen and oxygen with emphasis on new electrode materials, theoretical advances, and the development of experimental methods for light-driven water-splitting reactions has been discussed in Chapter 13 to identify stable, efficient, and cost-effective light-driven Photocatalytic systems. Now the challenge is to fabricate earth-abundant photoelectrodes and catalyst materials with high efficiency, good durability, and low cost. Recently, new visible-light-responsive photoelectrodes, including α - Fe_2O_3 , $BiVO_4$, WO_3 , CdS , C_3N_4 , and photoanodes have been tested for water splitting [106–109]. However, severe recombination of photogenerated electron–hole pairs on the surface results in poor performance of photocatalysts. Various attempts have been made to improve the performance of photocatalysts via doping, loading of cocatalysts, and heterojunctions [19, 57, 110–113]. Alivisatos and co-worker reported the design of multicomponent nanoheterostructures composed of platinum-tipped cadmium sulfide rod with an embedded cadmium selenide tips as highly active catalysts for hydrogen production with an apparent quantum yield of 20% at 450 nm [114]. Zhang *et al.* fabricated two-dimensional titania/cadmium sulfide heterostructures through a controlled sol–gel method with an excellent hydrogen evolution activity under visible-light irradiation and an apparent quantum yield of 6.9% at 420 nm [115]. Cao *et al.* developed a highly efficient and robust heterogeneous

photocatalytic material for hydrogen generation ($254\,000\ \mu\text{mol h}^{-1}\ \text{g}^{-1}$ for the initial 4.5 h) using the CoP/CdS hybrid catalyst in water under solar irradiation [116]. Kozlova *et al.* synthesized a multiphase photocatalyst $\text{Cd}_{1-x}\text{Zn}_x\text{S}/\text{TiO}_2$ with 3D ordered meso-/macroporous structure for H_2 evolution reaction from aqueous solutions of $\text{Na}_2\text{S}/\text{Na}_2\text{SO}_3$ under visible-light irradiation [117]. Zong *et al.* have employed MoS_2/CdS hybrid structure as a catalyst for photocatalytic H_2 evolution under visible-light irradiation [118]. Wang and co-workers developed shish-kebab-like multiheterostructured metal chalcogenides ($\text{CdS}-\text{Te}$, $\text{NiS}/\text{CdS}-\text{Te}$, and $\text{MoS}_2/\text{CdS}-\text{Te}$) photocatalysts to exhibit enhanced efficiency and stability toward photocatalytic H_2 generation due to intimate interactions between CdS and multicomponent cocatalysts, together with improved separation of photogenerated carriers due to the presence of Te nanotubes and trace CdTe [119]. A series of MoS_2 -based heterostructures, such as $\text{MoS}_2/\text{TiO}_2$ and $\text{MoS}_2/\text{graphene}$, have been tested for enhanced visible-light photocatalytic activities [87, 120]. Shen *et al.* showed one-dimensional MoS_2 nanosheet/porous TiO_2 nanowire hybrid nanostructures that facilitated charge separation and enhanced hydrogen generation rate of $16.7\ \text{mmol h}^{-1}\ \text{g}^{-1}$ in visible light. Chang *et al.* synthesized $\text{MoS}_2/\text{G}-\text{CdS}$ composite with an unexpected hydrogen evolution reaction activity. $\text{MoS}_2/\text{G}-\text{CdS}$ demonstrated as a promising photocatalyst with high efficiency and low cost for photocatalytic H_2 evolution reaction with a $1.8\ \text{mmol h}^{-1}$ H_2 evolution rate in lactic acid solution corresponding to an apparent quantum efficiency (AQE) of 28.1% at 420 nm, which is much higher than that of Pt/CdS in lactic acid solution. Graphitic carbon nitride, another carbon-based π -conjugated semiconductor material with a planar phase analogous to graphite, is also suitable for photocatalytic hydrogen production from water splitting made catalytic applications [121, 122]. However, quantum yields under visible light for H_2 production from water using g- C_3N_4 is still limited (not exceed 4%) due to the high recombination rate of the photoinduced electron-hole pair [91, 93]. Synthesis of porous g-CN, heteroatom-doped g-CN, metal-doped g-CN, structural modification with organic groups, metal oxide-g-CN composites, g-CN-graphene/CNT composites, and g-CN-based Z-scheme with enhanced photocatalytic activity for either H_2 or O_2 generation has been discussed in Chapter 12. Different nanostructured g-CN materials, such as nanosheets, nanospheres, and quantum dots, covalent organic frameworks (COFs), such as hydrazone COFs, donor-acceptor heptazine systems, and conjugated microporous polymers (CMPs) based on pyrene prepared from various C-C coupling reactions for water-splitting applications have also been focused in detail. Excellent performance was realized by hybridization of g- C_3N_4 with other cocatalysts. For example, metal sulfides, such as NiS, MoS_2 , WS_2 , and hydroxides, such as $\text{Ni}(\text{OH})_2$ and $\text{Co}(\text{OH})_2$, have been successfully deposited on g- C_3N_4 as cocatalysts for improved photocatalytic hydrogen production [123–126]. Meng *et al.* incorporated g- C_3N_4 into Ag_3PO_4 , which exhibited an improved catalytic activity for the degradation of methylene blue under visible-light irradiation [127]. The synergic effect between between g- C_3N_4 and Ag_3PO_4 led to structural stability for silver phosphate and high separation efficiency owing to the well-positioned CB and VB and consequently improved photocatalytic activity. Besides the single-phase and heterostructure-based photocatalysts,

Z-scheme photocatalyst, which contains two semiconductor photocatalyst systems, is another way to achieve efficient water splitting [128–130]. Each photocatalyst is responsible for one half reaction either H₂ or O₂ production or a new mediator to efficiently transfer charge between two photocatalysts that inhibit the fast unfavorable recombination of charge. Few examples of Z-scheme semiconductor–metal–semiconductor heterostructures have shown promising results for photocatalytic water splitting or CO₂ reduction [131, 132]. Notably, the electron storage and transport capabilities of graphene make it an effective mediator to separate the H₂ and O₂ evolution on different catalysts, such as ZnO, BiVO₄, CdS, TiO₂-based Z-scheme overall water splitting [133, 134]. Various other photocatalysts can be used as a hydrogen evolution photocatalyst in a Z-scheme water-splitting system, most notably nitrides and oxynitrides [135–138]. Chapter 13 provides a broad overview on photochemically induced water splitting to generate hydrogen and oxygen with various photocatalytic systems. However, the overall working efficiency in this Z-scheme is limited by the slow diffusion of redox couple ions and the competitive backward reactions between them. Moreover, “all-solid-state” Z-scheme based on ternary heterostructure of semiconductor–metal–semiconductor by using noble metals as the electron mediator to substitute solution-based redox couples has been also proposed [132, 139]. However, there is still a lack of solid evidence to verify the proposed Z-scheme electron transfer path.

1.4 Photocatalysis for Organic Transformations

The photocatalytic solar energy conversion has attracted increasing attention for organic transformations in order to develop environmentally friendly and new methodologies for selective redox organic synthesis at lower cost [140–142]. The visible-light-active photocatalysts, such as metal oxides, plasmonic photocatalysts, and polymeric carbon nitride, has been utilized for the selective redox organic transformations are classified as follows [143]:

- i) The oxidation of alcohols, amines, alkenes, and alkanes, the hydroxylation of aromatic compounds with O₂
- ii) The C_α–H bond activation and functionalization with nucleophiles to construct new C–C or C–X (X=O, N, or S) bonds
- iii) The reduction of nitrobenzenes to corresponding amino benzenes or azobenzenes with sacrificial agents under O₂-free conditions.

Metal oxides have been widely employed to achieve selective organic transformation under visible-light irradiation. For example, surface-modified TiO₂ with carboxyl group, such as ethylenediaminetetraacetic acid, or phenolic hydroxyl group could initiate photocatalytic redox reactions under visible-light irradiation [144, 145]. Visible-light-induced oxidation of alcohols to corresponding carbonyl compounds on anatase TiO₂ was reported by Higashimoto *et al.* [146] The selective formation of imines from primary amines was achieved under visible-light irradiation using high-surface-area anatase TiO₂ or Nb₂O₅

catalysts [147–149]. However, such organic transformation is limited by the adsorption of reactant molecule on the catalyst surface. In fact, activation of a sp^2 C—H bond in a benzene ring could not be achieved by this methodology. Metal oxides suffer from limited range of visible-light absorption. Furthermore, surface plasmon resonance (SPR)-induced nanostructured Au, Ag, and Cu supported on metal oxides provide an efficient pathway toward such photoredox organic transformation. Au/TiO₂ can be used as an efficient photocatalyst for the selective aerobic oxidation of alcohols in toluene or water under visible-light irradiation [150, 151]. Aromatic alcohols can be selectively transformed into corresponding aldehydes with O₂ in water using Au/CeO₂ as catalysts [152]. Additionally, a wide range of binary or tertiary metal oxides, such as TiO₂, WO₃, ZnO, In₂O₃, and SrTiO₃, have been tested as supports to carry out organic transformations under solvent-free conditions with high selectivity. However, the conversion efficiency was very low (0.5%) and plasmonic photocatalysts are more expensive. Alternatively, polymeric graphitic carbon nitride (g-C₃N₄) can be utilized as a metal-free visible-light photocatalyst for selective redox reactions at high temperature and O₂ pressure in addition to visible light [153, 154]. Aerobic oxidation of both aromatic alcohols and aliphatic alcohols into the corresponding aldehydes, selective oxidation of α -hydroxy ketones to 1,2-diketones and the oxidation of primary benzylic amines, and secondary benzylic amines to corresponding imines on mesoporous C₃N₄ have been achieved under visible-light irradiation at high temperature. It would be ideal to use room temperature for visible-light-induced organic synthesis; in fact, selective aerobic oxidation of organic substrates at room temperature has been reported with C₃N₄ as a photocatalyst [155]. Moreover, g-C₃N₄ can also act as the support material for transition metals and play an active role in the visible-light-induced hydroxylation of benzene with H₂O₂ [156]. Although g-C₃N₄ is stable, low-cost catalysts but elevated temperature and high O₂ pressure are required to achieve the desired conversions. Alternatively, organic dyes show potential photocatalytic activity for selective organic transformations under ambient conditions. The utilization of the organic dyes for visible-light-driven organic synthesis, which provides an energetically beneficial pathway, has been elaborated in Chapter 14. The photoredox catalytic methods for the activation of carbon–halogen bonds of both alkyl and aryl halides for systematically are described in Chapter 4. In this regard, various interesting strategies have been developed for visible-light-induced asymmetric redox catalysis in which efficient catalytic photochemical processes happened under stereochemical control and provide chiral molecules in an asymmetric manner for chemical transformation [157–161]. Moreover, novel asymmetric photoredox catalysts having the metal center simultaneously serve as the exclusive source of chirality, the catalytically active Lewis acid center, and the photoredox center, which offer new opportunities for the synthesis of nonracemic chiral molecules by visible light [162]. Hence, the development of visible-light-promoted photocatalytic reactions, which enable rapid and efficient synthesis of chemicals, is highly advantageous in terms of cost, safety, and environmental friendliness.

1.5 Mechanistic Studies of Visible-Light-Active Photocatalysis

In addition to the experimental observations, charge transfer mechanism across the semiconductor/semiconductor/metal junctions has been proposed and the resultant activity enhancement is also discussed [163]. The various techniques, such as transient-state surface photovoltage measurement, transient-state absorption spectra, and time-resolved microwave conductivity method (TRMC), are reviewed for photogenerated charge separation during catalysis [164]. The role of various active species, such as trapped electron and hole, superoxide radical and hydrogen peroxide ($\text{O}_2^{\bullet-}$ and H_2O_2), hydroxyl radical (OH^{\bullet}), singlet molecular oxygen ($^1\text{O}_2$) generated during catalysis, has been discussed in Chapter 17. A number of chemical probes are generally used to quantify the photocatalytic activity and also to indirectly identify the primary reactive species. The different theories concerning the nature of the active species are also conferred in view of the experimental results in Chapter 17.

Theoretical and computational models can be used to understand the electronic density of states and band structure of semiconductor in order to design a rational photocatalyst [165]. With high accuracy and decrease in computational costs, high-throughput computational screening has been utilized in order to realize the various aspects of photocatalytic reactions, such as light absorption, electron/hole transport, band edge alignment of semiconductors, and surface photoredox chemistry [166–171]. Computational methods are especially helpful for prediction of impurity states induced by dopants in tuning bandgaps in photocatalytic systems, such as TiO_2 [172]. In this regard, density functional theory (DFT) has been employed as a theoretical method to predict and understand the electronic structure of materials due to high accuracy and predictive power [173–175]. However, the inaccurate prediction of bandgaps is the major drawback of DFT. Additionally, time-dependent density functional theory (TD-DFT) is not widely used, and few studies implementing these methods are cluster-based models for water-splitting systems [176]. It is crucial to obtain a complete understanding of electron transfer phenomena to improve the performance of photocatalysts. The theoretical methods are being used to study the dynamics of charge separation, diffusion, relaxation, recombination, and related phenomena using *ab initio* nonadiabatic molecular dynamics [177]. Chapter 19 is dedicated to the computational modeling of photocatalysis, with an emphasis on reactive dynamics and quantum effects, such as zero-point energy, tunneling, and nonadiabatic transitions to predict excited-state electron-nuclear energy redistribution, nuclear dynamics, charge carrier dynamics, carrier recombination, and energy relaxation pathways in photocatalytic systems. Nevertheless, at present, computational screening studies on photoactive materials are very limited, which have the potential for the invention of novel materials.

A special chapter (Chapter 20) provides an overview of solar photocatalytic reactor designs on larger scale field and pilot-scale studies utilizing solar

illumination for the purification of water with nanoscale metal-oxide photocatalysts as well as their broader impacts on the environment. This chapter includes the design and fabrication of the various reactors with an emphasis on the barriers to the commercial application of this technology and environmental nanotoxicology for photocatalytic materials.

1.6 Summary

Design of nanoarchitectures and smart hybridization with specific active materials has emerged as an interesting platform for light-harvesting and visible-light-driven photocatalysis. The current status of research on nanostructures of common semiconducting materials has been highlighted for photocatalytic energy conversion and utilization including photocatalytic water splitting and CO₂ reduction, and other photo-assisted reactive applications, such as pollutant degradation, selective conversion of organic compounds, and biological disinfection. In the past few years, much progress has been made in the design and synthesis of functional materials based on either metal oxides or semiconductors to achieve efficient light-harvesting capacity. Research in this area is continuing to grow with the objective of tuning the intrinsic properties of catalysts, such as excellent light absorption, rapid charge separation, transport, and collection, as well as rapid kinetics of interfacial reactions and mass transport of reactants in nanodimension. The advanced functionality and improved performance for practical applications of the visible-light-active nanostructured catalysts have been also highlighted. Here, key areas are identified that will need particular attention as the search continues for stable, efficient, and cost-effective light-driven photoelectrolysis systems that exploit electron/hole separation in semiconductor/electrolyte junctions. Synergistic and cooperative interactions among different functionalities in nanohybrids open novel strategy for designing molecular materials for photocatalysis, light harvesting, and artificial photosynthesis. Careful selection of a specific combination of semiconductors to obtain desired band-gap energy would demonstrate successful synthesis of high-quality hybrid nanostructures with enhanced photostability and photocatalytic efficiency. It may be concluded that hybrid nanostructures containing diverse functionalities and active materials will be assembled to harvest solar light for future energy crisis and water splitting or carbon dioxide reduction with energy input from sunlight. Moreover, the efficiency of photocatalytic reduction of CO₂ could be deactivated after long irradiation; therefore, it is necessary to pay more attention on the semiconductor deactivation issue in future work. Until now, there have been few reports dealing with the interpretation and theory background behind the observed collective phenomena of heterostructures. Theoretical studies would lead to rational improvement of band structure and morphological design of photocatalytic materials for the discovery of new materials.

References

- 1 Xie, W.T., Dai, Y.J., Wang, R.Z., and Sumathy, K. (2011) Concentrated solar energy applications using Fresnel lenses: a review. *Renew. Sustain. Energy Rev.*, **15**, 2588–2606.
- 2 Turner, J.A. (2004) Sustainable hydrogen production. *Science*, **305**, 972–974.
- 3 Legrini, E.O. and Braun, A.M. (1993) Photochemical processes for water treatment. *Chem. Rev.*, **93**, 671–698.
- 4 Mahaney, O.O.P., Murakami, N., Abe, R., and Ohtani, B. (2009) Correlation between photocatalytic activities and structural and physical properties of titanium(IV) oxide powders. *Chem. Lett.*, **38**, 238–239.
- 5 Wang, Z., Chen, C., Ma, W., and Zhao, J. (2013) Sensitization of titania semiconductor: a promising strategy to utilize visible light, in *Photocatalysis and Water Purification: From Fundamentals to Recent Applications* (ed. P. Pichat), Wiley-VCH, New York.
- 6 Abe, R. (2013) Z-scheme type water splitting into H₂ and O₂ under visible light through two-step photoexcitation between two different photocatalysts, in *New and Future Developments in Catalysis, Solar Photocatalysis* (ed. S.L. Suib), Elsevier, pp. 341–370.
- 7 Weng, L., Zhang, H., Govorov, A.O., and Ouyang, M. (2014) Hierarchical synthesis of non-centrosymmetric hybrid nanostructures and enabled plasmon-driven photocatalysis. *Nat. Commun.*, **5**, 4792–4602.
- 8 Zhang, N., Zhang, Y., and Xu, Y.-J. (2012) Recent progress on graphene-based photocatalysts: current status and future perspectives. *Nanoscale*, **4**, 5792–5813.
- 9 Li, X., Yu, J., Wageh, S., Al-Ghamdi, A.A., and Xie, J. (2016) Graphene in photocatalysis: a review. *Small*, **12**, 6640–6696.
- 10 Coronado, J., Fresno, F., Hernández-Alonso, M.D., and Portela, R. (eds) (2013) *Design of Advanced Photocatalytic Materials for Energy and Environmental Applications*, Green Energy and Technology, Springer, pp. 1–101.
- 11 Schneider, J., Matsuoka, M., Takeuchi, M., Zhang, J., Horiuchi, Y., Anpo, M., and Bahnemann, D.W. (2014) Understanding TiO₂ photocatalysis: mechanisms and materials. *Chem. Rev.*, **114**, 9919–9986.
- 12 Guo, Q., Zhou, C., Ma, Z., Ren, Z., Fan, H., and Yang, X. (2016) Elementary photocatalytic chemistry on TiO₂ surfaces. *Chem. Soc. Rev.*, **45**, 3701–3730.
- 13 Qu, Y. and Duan, X. (2013) Progress, challenge and perspective of heterogeneous photocatalysts. *Chem. Soc. Rev.*, **42**, 2568–2580.
- 14 Asahi, R., Morikawa, T., Irie, H., and Ohwaki, T. (2014) Nitrogen-doped titanium dioxide as visible-light-sensitive photocatalyst: designs, developments, and prospects. *Chem. Rev.*, **114**, 9824–9852.
- 15 Kowalska, E., Yoshiiri, K., Wei, Z., Zheng, S., Kast, E., Remita, H., Ohtani, B., and Rau, S. (2015) Hybrid photocatalysts composed of titania modified with plasmonic nanoparticles and ruthenium complexes for decomposition of organic compounds. *Appl. Catal. B*, **178**, 133–143.

- 16 Kouamé, N.A., TahiriAlaoui, O., Herissan, A., Larios, E., José-Yacaman, M., Etcheberry, A., Colbeau-Justin, C., and Remita, H. (2015) Visible light-induced photocatalytic activity of modified titanium(IV) oxide with zero valent bismuth clusters. *New J. Chem.*, **39**, 2316–2322.
- 17 Kale, M.J., Avanesian, T., and Christopher, P. (2014) Direct photocatalysis by plasmonic nanostructures. *ACS Catal.*, **4**, 116–128.
- 18 And, X.J. and Xiao, W.-J. (2012) Visible-light photoredox catalysis. *Angew. Chem. Int. Ed.*, **51**, 2–13.
- 19 Wang, Y., Wang, Q., Zhan, X., Wang, F., Safdar, M., and He, J. (2013) Visible light driven type II heterostructures and their enhanced photocatalysis properties: a review. *Nanoscale*, **5**, 8326–8339.
- 20 Pelaez, M., Nolan, N., Pillai, S., Seery, M., and Falaras, P. (2012) A review on the visible light active titanium dioxide photocatalysts for environmental applications. *Appl. Catal. B*, **125**, 331–349.
- 21 Kositzi, M., Poullos, I., Malato, S., Caceres, J., and Campos, A. (2004) Solar photocatalytic treatment of synthetic municipal wastewater. *Water Res.*, **38**, 1147–1154.
- 22 Reddy, P.A.K., Reddy, P.V.L., Kwon, E., Kim, K.-H., Akter, T., and Kalagar, S. (2016) Recent advances in photocatalytic treatment of pollutants in aqueous media. *Environ. Int.*, **91**, 94–103.
- 23 Fujishima, A., Zhang, X., and Tryk, D.A. (2007) Heterogeneous photocatalysis: From water photolysis to applications in environmental cleanup. *Int. J. Hydrogen Energy*, **32**, 2664–2672.
- 24 Kubacka, A., Fernandez-Garcia, M., and Colon, G. (2012) Advanced nanoarchitectures for solar photocatalytic applications. *Chem. Rev.*, **112**, 1555–1614.
- 25 Kamat, P.V. (2012) TiO₂ nanostructures: recent physical chemistry advances. *J. Phys. Chem. Lett.*, **3**, 663–672.
- 26 Li, L., Yan, J., Wang, T., Zhao, Z.-J., Zhang, J., Gong, J., and Guan, N. (2015) Sub-10 nm rutile titaniumdioxide nanoparticles for efficient visible-light-driven photocatalytic hydrogen production. *Nat. Commun.*, **6**, 5881–5891.
- 27 Tao, J., Luttrell, T., and Batzill, M. (2011) A two-dimensional phase of TiO₂ with a reduced bandgap. *Nat. Chem.*, **3**, 296–300.
- 28 Linic, S., Christopher, P., and Ingram, D.B. (2011) Plasmonic-metal nanostructures for efficient conversion of solar to chemical energy. *Nat. Mater.*, **10**, 911–921.
- 29 Grabowska, E., Zaleska, A., Sorgues, S., Kunst, M., Etcheberry, A., Colbeau-Justin, C., and Remita, H. (2013) Modification of titanium(IV) dioxide with small silver nanoparticles: application in photocatalysis. *J. Phys. Chem. C*, **117**, 1955–1962.
- 30 Hai, Z., Kolli, N.E., Uribe, D.B., Beaunier, P., José-Yacaman, M., Vigneron, J., Etcheberry, A., Sorgues, S., Colbeau-Justin, C., And, C.J., and Remita, H. (2013) Modification of TiO₂ by bimetallic Au–Cu nanoparticles for waste water treatment. *J. Mater. Chem. A.*, **1**, 10829–10835.
- 31 Chen, X., Liu, L., Yu, P.Y., and Mao, S.S. (2011) Increasing solar absorption for photocatalysis with black hydrogenated titanium dioxide nanocrystals. *Science*, **331**, 746–750.

- 32 Liu, X., Zhu, G., Wang, X., Yuan, X., Lin, T., and Huang, F. (2016) Progress in black titania: a new material for advanced photocatalysis. *Adv. Energy Mater.*, **6**, 1600452.
- 33 Ullattil, S.G. and Periyat, P. (2015) Green microwave switching from oxygen rich yellow anatase to oxygen vacancy rich black anatase TiO₂ solar photocatalyst using Mn(II) as 'anatase phase purifier'. *Nanoscale*, **7**, 19184–19192.
- 34 Etacheri, V., Seery, M.K., Hinder, S.J., and Pillai, S.C. (2011) Oxygen rich titania: a dopant free, high temperature stable, and visible-light active anatase photocatalyst. *Adv. Funct. Mater.*, **21**, 3744–3752.
- 35 Paek, M.-J., Woo Kim, T., and Hwang, S.-J. (2008) Effects of hydronium intercalation and cation substitution on the photocatalytic performance of layered titanium oxide. *J. Phys. Chem. Solids*, **69**, 1444–1446.
- 36 Kong, X., Zeng, C., Wang, X., Huang, J., Li, C., Fei, J., Li, J., and Feng, Q. (2016) Ti—O—O coordination bond caused visible light photocatalytic property of layered titanium oxide. *Sci. Rep.*, **6**, 29049.
- 37 Gao, S.Y., Ueno, K., and Misawa, H. (2011) Plasmonic antenna effects on photochemical reactions. *Acc. Chem. Res.*, **44**, 251–260.
- 38 Tian, Y. and Tatsuma, T. (2005) Mechanisms and applications of plasmon-induced charge separation at TiO₂ films loaded with gold nanoparticles. *J. Am. Chem. Soc.*, **127**, 7632–7637.
- 39 Liu, Z.W., Hou, W.B., Pavaskar, P., Aykol, M., and Cronin, S.B. (2011) Plasmon resonant enhancement of photocatalytic water splitting under visible illumination. *Nano Lett.*, **11**, 1111–1116.
- 40 Ingram, D.B. and Linic, S. (2011) Water splitting on composite plasmonic-metal/semiconductor photoelectrodes: evidence for selective plasmon-induced formation of charge carriers near the semiconductor surface. *J. Am. Chem. Soc.*, **133**, 5202–5205.
- 41 Khalil, L.B., Mourad, W.E., and Rophael, M.W. (1998) Photo-catalytic reduction of environmental pollutant Cr(VI) over some semiconductors under UV/visible light illumination. *Appl. Catal. B*, **17**, 267–273.
- 42 Garza-Arévalo, J.I., García Montes, I., Hinojosa Reyes, M., Guzmán Mar, J.L., Rodríguez González, V., and Reyes, L.H. (2016) Fe doped TiO₂ photocatalyst for the removal of As(III) under visible radiation and its potential application on the treatment of As-contaminated ground water. *Mater. Res. Bulletin*, **73**, 145–152.
- 43 Wu, Q., Zhao, J., Qin, G., Wang, C., Tong, X., and Xue, S. (2013) Photocatalytic reduction of Cr(VI) with TiO₂ film under visible light. *Appl. Catal. B*, **142**, 142–148.
- 44 Cohen, M.D., Kargacin, B., Klein, C.B., and Costa, M. (1993) Mechanisms of chromium carcinogenicity and toxicity. *Crit. Rev. Toxicol.*, **23**, 255–281.
- 45 Jacobs, J.A. and Testa, S.M. (2005) Overview of chromium(VI) in the environment: background and history, in *Chromium (VI) Handbook* (eds J. Guertin, J.A. Jacobs, and C.P. Avakian), CRC Press, Boca Raton, FL, pp. 1–22.
- 46 AlOtaibi, B., Fan, S., Wang, D., Ye, J., and Mi, Z. (2015) Wafer-level artificial photosynthesis for CO₂ reduction into CH₄ and CO using GaN nanowires. *ACS Catal.*, **5**, 5342–5348.

- 47 Inoue, T., Fujishima, A., Konishi, S., and Honda, K. (1979) Photoelectrocatalytic reduction of carbon dioxide in aqueous suspensions of semiconductor powders. *Nature*, **277**, 637–638.
- 48 Tu, W., Zhou, Y., and Zou, Z. (2014) Photocatalytic Conversion of CO₂ into renewable hydrocarbon fuels: state-of-the-art accomplishment, challenges, and prospects. *Adv. Mater.*, **26**, 4607–4626.
- 49 Habisreutinger, S.N., Schmidt-Mende, L., and Stolarczyk, J.K. (2013) Photocatalytic reduction of CO₂ on TiO₂ and other semiconductors. *Angew. Chem. Int. Ed.*, **52**, 7372–7408.
- 50 Kondratenko, E.V., Mul, G., Baltrusaitis, J., Larrazábal, G.O., and Pérez-Ramírez, J. (2013) Status and perspectives of CO₂ conversion into fuels and chemicals by catalytic, photocatalytic and electrocatalytic processes. *Energy Environ. Sci.*, **6**, 3112–3135.
- 51 Kowalska, E., Wei, Z., Karabiyik, B., Herissan, A., Janczarek, M., Endo, M., Markowska-Szczupak, A., Remita, H., and Ohtani, B. (2015) Silver-modified titania with enhanced photocatalytic and antimicrobial properties under UV and visible light irradiation. *Catal. Today*, **252**, 136–142.
- 52 Awazu, K., Fujimaki, M., Rockstuhl, C., Tominaga, J., Mu-rakami, H., Ohki, Y., Yoshida, N., and Watanabe, T. (2008) A plasmonic photocatalyst consisting of silver nanoparticles embedded in titanium dioxide. *J. Am. Chem. Soc.*, **130**, 1676–1680.
- 53 Wang, P., Huang, B. B., Qin, X. Y., Zhang, X. Y., Dai, Y., Wei, J. and Whangbo, M.-H. (2008) Ag@AgCl: A highly efficient and stable photocatalyst active under visible light. *Angew. Chem. Int. Ed.*, **47**, 7931–7933.
- 54 Ghosh, S., Kouamé, N.A., Ramos, L., Remita, S., Dazzi, A., Deniset-Besseau, A., Beaunier, P., Goubard, F., Aubert, P.-H., and Remita, H. (2015) Conducting polymer nanostructures for photocatalysis under visible light. *Nat. Mater.*, **14**, 505–511.
- 55 Ghosh, S., Kouame, N.A., Remita, S., Ramos, L., Goubard, F., Aubert, P.-H., Dazzi, A., Deniset-Besseau, A., and Remita, H. (2015) Visible-light active conducting polymer nanostructures with superior photocatalytic activity. *Sci. Rep.*, **5**, 18002–18011.
- 56 Floresyona, D., Goubard, F., Aubert, P.-H., Lampr, I., Mathurin, J., Dazzi, A., Ghosh, S., Beaunier, P., Brisset, F., Remita, S., Ramos, L., and Remita, H. (2017) Highly active poly(3-hexylthiophene) nanostructures for photocatalysis under solar light. *Appl. Catal. B*, **209**, 23–32.
- 57 Marschall, R. (2014) Semiconductor composites: strategies for enhancing charge carrier separation to improve photocatalytic activity. *Adv. Funct. Mater.*, **24**, 2421–2440.
- 58 Tran, P.D., Wong, L.H., Barber, J., and Loo, J.S.C. (2012) Recent advances in hybrid photocatalysts for solar fuel production. *Energy Environ. Sci.*, **5**, 5902–5918.
- 59 Yuan, Y.-P., Ruan, L.-W., Barber, J., Chye, S., Loo, J., and Xue, C. (2014) Hetero-nanostructured suspended photocatalysts for solar-to-fuel conversion. *Energy Environ. Sci.*, **7**, 3934–3951.

- 60 Park, Y., McDonald, K.J., and Choi, K.S. (2013) Progress in bismuth vanadate photoanodes for use in solar water oxidation. *Chem. Soc. Rev.*, **42**, 2321–2337.
- 61 Li, L., Salvador, P.A., and Rohrer, G.S. (2014) Photocatalysts with internal electric fields. *Nanoscale*, **6**, 24–42.
- 62 Zou, J.P., Lei, S.L., Yu, J., Luo, S.L., Luo, X.B., Tang, X.H., Dai, W.L., Sun, J., Guo, G.C., and Au, C.T. (2014) Highly efficient and stable hydrogen evolution from water with CdS as photosensitizer – a noble-metal-free system. *Appl. Catal. B*, **150–151**, 466–471.
- 63 Park, H., Choi, W., and Hoffmann, M.R. (2008) Effects of the preparation method of the ternary CdS/TiO₂/Pt hybrid photocatalysts on visible light-induced hydrogen production. *J. Mater. Chem.*, **18**, 2379–2385.
- 64 Wang, C.J., Thompson, R.L., Baltrus, J., and Matranga, C. (2010) Visible light photoreduction of CO₂ using CdSe/Pt/TiO₂ heterostructured catalysts. *J. Phys. Chem. Lett.*, **1**, 48–53.
- 65 Wang, Z.L., Liu, Y.X., Martin, D.J., Wang, W.D., Tang, J.W., and Huang, W.X. (2013) CuO_x–TiO₂ junction: what is the active component for photocatalytic H₂ production? *Chem. Chem. Phys.*, **15**, 14956–14960.
- 66 Asi, M.A., He, C., Su, M.H., Xia, D.H., Lin, L., Deng, H.Q., Xiong, Y., Qiu, R.L., and Li, X.Z. (2011) Photocatalytic reduction of CO₂ to hydrocarbons using AgBr/TiO₂ nanocomposites under visible light. *Catal. Today*, **175**, 256–263.
- 67 Wang, C.J., Thompson, R.L., Ohodnicki, P., Baltrus, J., and Matranga, C. (2011) Size-dependent photocatalytic reduction of CO₂ with PbS quantum dot sensitized TiO₂ heterostructured photocatalysts. *J. Mater. Chem.*, **21**, 13452–13457.
- 68 Sardar, S., Kar, P., Remita, H., Liu, B., Lemmens, P., Pal, S.K., and Ghosh, S. (2015) Enhanced charge separation and FRET at heterojunctions between semiconductor nanoparticles and conducting polymer nanofibers for efficient solar light harvesting. *Sci. Rep.*, **5**, 17313–17327.
- 69 Razgoniaeva, N., Moroz, P., Lambright, S., and Zamkov, M. (2015) Photocatalytic applications of colloidal heterostructured nanocrystals: what's next? *J. Phys. Chem. Lett.*, **6**, 4352–4359.
- 70 Basu, M., Garg, N., and Ganguli, A.K. (2014) A type-II semiconductor (ZnO/CuS heterostructure) for visible light photocatalysis. *J. Mater. Chem. A*, **2**, 7517–7525.
- 71 Gao, M.-R., Xu, Y.-F., Jiang, J., and Yu, S.-H. (2013) Nanostructured metal chalcogenides: synthesis, modification, and applications in energy conversion and storage devices. *Chem. Soc. Rev.*, **42**, 2986–3017.
- 72 Wang, J.G., Li, X.R., Zhu, J., Li, X., and Li, H. (2013) Mesoporous yolk–shell SnS₂–TiO₂ visible photocatalysts with enhanced activity and durability in Cr(VI) reduction. *Nanoscale*, **5**, 1876–1881.
- 73 Ghosh, S., Holade, Y., Remita, H., Servat, K., Beaunier, P., Hagège, A., Kokoh, B. and Napporn, T. W. (2016) Facile synthesis of surfactant-free graphene supported gold based nanocomposites: Robust catalysts for glucose oxidation. *Electrochim. Acta*, **212**, 864–875.

- 74 Sardar, S., Ghosh, S., Remita, H., Kar, P., Liu, B., Lemmens, P., and Pal, S.K. (2016) Reduced graphene oxides–metal composites as counter electrode in dye-sensitized solar cells. *RSC Adv.*, **6**, 33433–33442.
- 75 Jiang, X., Nisar, J., Pathak, B., Zhao, J., and Ahuja, R. (2013) Graphene oxide as a chemically tunable 2-D material for visible-light photocatalyst applications. *J. Catal.*, **299**, 204–209.
- 76 Dreyer, D.R., Park, S., Bielawski, C.W., and Ruoff, R.S. (2010) The chemistry of graphene oxide. *Chem. Soc. Rev.*, **39**, 228–240.
- 77 Low, J., Yu, J., and Ho, W. (2015) Graphene-based photocatalysts for CO₂ reduction to solar fuel. *J. Phys. Chem. Lett.*, **6**, 4244–4251.
- 78 Yang, M.-Q. and Xu, Y.-J. (2016) Photocatalytic conversion of CO₂ over graphene-based composites: current status and future perspective. *Nanoscale Horiz.*, **1**, 185–200.
- 79 Liang, Y.T., Vijayan, B.K., Gray, K.A., and Hersam, M.C. (2011) Minimizing graphene defects enhances titania nanocomposite-based photocatalytic reduction of CO₂ for improved solar fuel production. *Nano Lett.*, **11**, 2865–2870.
- 80 Yu, J.G., Jin, J., Cheng, B., and Jaroniec, M. (2014) A noble metal-free reduced graphene oxide–CdS nanorod composite for the enhanced visible-light photocatalytic reduction of CO₂ to solar fuel. *J. Mater. Chem. A*, **2**, 3407–3416.
- 81 Meng, F., Li, J., Cushing, S.K., Bright, J., Zhi, M., Rowley, J.D., Hong, Z., Manivannan, A., Bristow, A.D., and Wu, N. (2013) Photocatalytic water oxidation by hematite/reduced graphene oxide composites. *ACS Catal.*, **3**, 746–751.
- 82 Li, Z., Shen, Y., Guan, Y., Hu, Y., Lin, Y., and Nan, C.W. (2014) Bandgap engineering and enhanced interface coupling of graphene–BiFeO₃ nanocomposites as efficient photocatalysts under visible light. *J. Mater. Chem. A*, **2**, 1967–1973.
- 83 Yang, Y., Ren, L., Zhang, C., Huang, S., and Liu, T. (2011) Facile fabrication of functionalized graphene sheets (FGS)/ZnO nanocomposites with photocatalytic property. *ACS Appl. Mater. Interfaces*, **3**, 2779–2785.
- 84 Zhang, N., Zhang, Y., Pan, X., Fu, X., Liu, S., and Xu, Y.J. (2011) Assembly of CdS nanoparticles on the two-dimensional graphene scaffold as visible-light-driven photocatalyst for selective organic transformation under ambient conditions. *J. Phys. Chem. C*, **115**, 23501–23511.
- 85 Han, W., Ren, L., Qi, X., Liu, Y., Wei, X., Huang, Z., and Zhong, J. (2014) Synthesis of CdS/ZnO/graphene composite with high-efficiency photoelectrochemical activities under solar radiation. *Appl. Surf. Sci.*, **299**, 12–18.
- 86 Zong, X., Yan, H., Wu, G., Ma, G., Wen, F., Wang, L., and Li, C. (2008) Enhancement of photocatalytic H₂ evolution on CdS by loading MoS₂ as cocatalyst under visible light irradiation. *J. Am. Chem. Soc.*, **130**, 7176–7177.
- 87 Chang, K., Mei, Z., Wang, T., Kang, Q., Ouyang, S., and Ye, J. (2014) MoS₂/graphene cocatalyst for efficient photocatalytic H₂ evolution under visible light irradiation. *ACS Nano*, **8**, 7078–7087.
- 88 Cravanzola, S., Muscuso, L., Cesano, F., Agostini, G., Damin, A., Scarano, D., and Zecchina, A. (2015) MoS₂ nanoparticles decorating titanate-nanotube

- surfaces: combined microscopy, spectroscopy, and catalytic studies. *Langmuir*, **31**, 5469–5478.
- 89 Zhou, W., Yin, Z., Du, Y., Huang, X., Zeng, Z., Fan, Z., Liu, H., Wang, J., and Zhang, H. (2013) Synthesis of few-layer MoS₂ nanosheet coated TiO₂ nanobelt heterostructures for enhanced photocatalytic activities. *Small*, **9**, 140–147.
- 90 Xia, J., Ge, Y., Zhao, D., Di, J., Ji, M., Yin, S., Li, H., and Chen, R. (2015) Microwave-assisted synthesis of few-layered MoS₂/BiOBr hollow microspheres with superior visible-light-response photocatalytic activity for ciprofloxacin removal. *Cryst.EngComm.*, **17**, 3645–3651.
- 91 Wang, X., Maeda, K., Thomas, A., Takanabe, K., Xin, G., Carlson, J.M., Domen, K., and Antonietti, M. (2009) A metal-free polymeric photocatalyst for hydrogen production from water under visible light. *Nat. Mater.*, **8**, 76–80.
- 92 Kroke, E., Schwarz, M., Horath-Bordon, E., Kroll, P., Noll, B., and Norman, A.D. (2002) Tri-s-triazine to graphitic C₃N₄ structures. *New J. Chem.*, **26**, 508–512.
- 93 Zhang, Y., Mon, T., and Ye, J. (2012) Polymeric carbon nitrides: semiconducting properties and emerging applications in photocatalysis and photoelectrochemical energy conversion. *Sci. Adv. Mater.*, **4**, 282–291.
- 94 Maeda, K., Kuriki, R., Zhang, M., Wang, X., and Ishitani, O. (2014) The effect of the pore-wall structure of carbon nitride on photocatalytic CO₂ reduction under visible light. *J. Mater. Chem. A*, **2**, 15146–11151.
- 95 Zhou, S., Liu, Y., Li, J., Wang, Y., Jiang, G., Zhao, Z., Wang, D., Duan, A., Liu, J., and Wei, Y. (2014) Facile in situ synthesis of graphitic carbon nitride (g-C₃N₄)-N-TiO₂ heterojunction as an efficient photocatalyst for the selective photoreduction of CO₂ to CO. *Appl. Catal. B*, **157–158**, 20–29.
- 96 He, Y., Wang, Y., Zhang, L., Teng, B., and Fan, M. (2015) High-efficiency conversion of CO₂ to fuel over ZnO/g-C₃N₄ photocatalyst. *Appl. Catal. B*, **167–168**, 1–8.
- 97 Cao, S., Liu, X., Yuan, Y., Zhang, Z., Liao, Y., Fang, J., Loo, S.C.J., Sum, T.C., and Xue, C. (2014) Solar-to-fuels conversion over In₂O₃/g-C₃N₄ hybrid photocatalysts. *Appl. Catal., B*, **146–147**, 940–946.
- 98 Li, M., Zhang, L., Fan, X., Zhou, Y., Wu, M., and Shi, J. (2015) Highly selective CO₂ photoreduction to CO over g-C₃N₄/Bi₂WO₆ composites under visible light. *J. Mater. Chem. A*, **3**, 5189–5196.
- 99 Vinodgopal, K., Wynkoop, D. E., and Kamat, P. V. (1996) Environmental photochemistry on semiconductor surfaces: photosensitized degradation of a textile azo dye, Acid Orange 7, on TiO₂ particles using visible light. *Environ. Sci. Technol.*, **30**, 1660–1666.
- 100 Duan, M.-y., Li, J., Mele, G., Wang, C., Lü, X.-f., Vasapollo, G. and Zhang, F.-x. (2010) Photocatalytic activity of novel tin porphyrin/TiO₂ based composites. *J. Phys. Chem. C*, **114**, 7857–62.
- 101 Oregan, B. and Gratzel, M. (1991) A low-cost, high-efficiency solar-cell based on dye-sensitized colloidal TiO₂ films. *Nature*, **353**, 737–740.
- 102 Gratzel, M. (1981) Artificial photosynthesis: water cleavage into hydrogen and oxygen by visible light. *Acc. Chem. Res.*, **14**, 376–384.

- 103 Chen, X.B., Shen, S.H., Guo, L.J., and Mao, S.S. (2010) Semiconductor-based photocatalytic hydrogen generation. *Chem. Rev.*, **110**, 6503–6570.
- 104 Kudo, A. and Miseki, Y. (2009) Heterogeneous photocatalyst materials for water splitting. *Chem. Soc. Rev.*, **38**, 253–278.
- 105 Zou, Z., Ye, J., Sayama, K., and Arakawa, H. (2001) Direct splitting of water under visible light irradiation with an oxide semiconductor photocatalyst. *Nature*, **414**, 625–627.
- 106 Ni, M., Leung, M.K.H., Leung, D.Y.C., and Sumathy, K. (2007) A review and recent developments in photocatalytic water-splitting using TiO_2 for hydrogen production. *Renew. Sustain. Energy Rev.*, **11**, 401–425.
- 107 Sivula, K. and van de Krol, R. (2016) Semiconducting materials for photoelectrochemical energy conversion. *Nat. Rev. Mater.*, **70**, 15010:1–15010:7.
- 108 Kay, A., Cesar, I., and Gratzel, M. (2006) New benchmark for water photooxidation by nanostructured $\alpha\text{-Fe}_2\text{O}_3$ Films. *J. Am. Chem. Soc.*, **128**, 15714–15721.
- 109 Liang, Y., Tsubota, T., Mooij, L.P.A., and van de Krol, R. (2011) Highly improved quantum efficiencies for thin film BiVO_4 photoanodes. *J. Phys. Chem. C*, **115**, 17594–17598.
- 110 Chen, Y., Zhao, S., Wang, X., Peng, Q., Lin, R., Wang, Y., Shen, R., Cao, X., Zhang, L., Zhou, G., Li, J., Xia, A., and Li, Y. (2016) Synergetic integration of $\text{Cu}_{1.94}\text{S}-\text{Zn}_x\text{Cd}_{1-x}\text{S}$ heteronanorods for enhanced visible-light-driven photocatalytic hydrogen production. *J. Am. Chem. Soc.*, **138**, 4286–4289.
- 111 Bao, J. (2015) Photoelectrochemical water splitting: a new use for bandgap engineering. *Nat. Nanotechnol.*, **10**, 19–20.
- 112 Li, J., Hoffmann, M.W.G., Shen, H., Fabrega, C., Prades, J.D., Andreu, T., Hernandez-Ramirez, F., and Mathur, S. (2012) Enhanced photoelectrochemical activity of an excitonic staircase in CdS@TiO_2 and $\text{CdS@anatase@rutile TiO}_2$ heterostructures. *J. Mater. Chem.*, **22**, 20472–20476.
- 113 Qiu, F., Han, Z.P., Jeffrey, J.O., Michael, Y.S., Kelly, L., and Krauss, T.D. (2016) Photocatalytic hydrogen generation by CdSe/CdS nanoparticles. *Nano Lett.*, **16**, 5347–5352.
- 114 Amirav, L. and Alivisatos, A.P. (2010) Photocatalytic hydrogen production with tunable nanorod heterostructures. *J. Phys. Chem. Lett.*, **1**, 1051–1054.
- 115 Zhang, J., Zhu, Z., Tang, Y., Müllen, K., and Feng, X. (2014) Titania nanosheet-mediated construction of a two-dimensional titania/cadmium sulfide heterostructure for high hydrogen evolution activity. *Adv Mater.*, **26**, 734–738.
- 116 Cao, S., Chen, Y., Wang, C.-J., Lv, X.-J., and Fu, W.-F. (2015) Spectacular photocatalytic hydrogen evolution using metal-phosphide/ CdS hybrid catalysts under sunlight irradiation. *Chem. Commun.*, **51**, 8708–8711.
- 117 Kozlova, E.A., Kurenkova, A.Y., Semeykina, V.S., Parkhomchuk, E.V., Cherepanova, S.V., Gerasimov, E.Y., Saraev, A.A., Kaichev, V.V., and Parmon, V.N. (2015) Effect of titania regular macroporosity on the photocatalytic hydrogen evolution on $\text{Cd}_{1-x}\text{Zn}_x\text{S}/\text{TiO}_2$ catalysts under visible light. *ChemCatChem.*, **7**, 4108–4117.

- 118 Zong, X., Wu, G., Yan, H., Ma, G., Shi, J., Wen, F., Wang, L., and Li, C. (2010) Photocatalytic H₂ evolution on MoS₂/CdS catalysts under visible light irradiation. *J. Phys. Chem. C*, **114**, 1963–1972.
- 119 Hu, J., Liu, A., Jin, H., Ma, D., Yin, D., Ling, P., Wang, S., Lin, Z., and Wang, J. (2015) A versatile strategy for shish-kebab-like multi-heterostructured chalcogenides and enhanced photocatalytic hydrogen evolution. *J. Am. Chem. Soc.*, **137**, 11004–11010.
- 120 Shen, M., Yan, Z., Yang, L., Du, P., Zhang, J., and Xiang, B. (2014) MoS₂ nanosheet/TiO₂ nanowire hybrid nanostructures for enhanced visible-light photocatalytic activities. *Chem. Commun.*, **50**, 15447–15449.
- 121 Thomas, A., Fischer, A., Goettmann, F., Antonietti, M., Muller, J.O., Schlogl, R., and Carlsson, J.M. (2008) Graphitic carbon nitride materials: variation of structure and morphology and their use as metal-free catalysts. *J. Mater. Chem.*, **18**, 4893–4908.
- 122 Hu, J., Cheng, W., Huang, S., Wu, D., and Xie, Z. (2006) First-principles modelling of nonlinear optical properties of C₃N₄ polymorphs. *Appl. Phys. Lett.*, **89**, 261117.
- 123 Chen, Z., Sun, P., Fan, B., Zhang, Z., and Fang, X. (2014) In Situ template-free ion-exchange process to prepare visible-light-active g-C₃N₄/NiS hybrid photocatalysts with enhanced hydrogen evolution activity. *J. Phys. Chem. C*, **118**, 7801–7807.
- 124 Hou, Y., Laursen, A.B., Zhang, J., Zhang, G., Zhu, Y., Wang, X., Dahl, S., and Chorkendorff, I. (2013) Layered nanojunctions for hydrogen-evolution catalysis. *Angew. Chem. Int. Ed.*, **52**, 3621–3625.
- 125 Hou, Y., Zhu, Y., Xu, Y., and Wang, X. (2014) Photocatalytic hydrogen production over carbon nitride loaded with WS₂ as cocatalyst under visible light. *Appl. Catal., B*, **156–157**, 122–127.
- 126 Yu, J., Wang, S., Cheng, B., Lin, Z., and Huang, F. (2013) Noble metal-free Ni(OH)₂-g-C₃N₄ composite photocatalyst with enhanced visible-light photocatalytic H₂-production activity. *Catal. Sci. Technol.*, **3**, 1782–1789.
- 127 Meng, S., Ning, X., Zhang, T., Chen, S.-F., and Fu, X. (2015) What is the transfer mechanism of photogenerated carriers for the nanocomposite photocatalyst Ag₃PO₄/g-C₃N₄, band-band transfer or a direct Z-scheme? *Phys. Chem. Chem. Phys.*, **17**, 11577–11585.
- 128 Sasaki, Y., Nemoto, H., Saito, K., and Kudo, A. (2009) Solar water splitting using powdered photocatalysts driven by Z-schematic interparticle electron transfer without an electron mediator. *J. Phys. Chem. C*, **113**, 17536–17542.
- 129 Maeda, K. (2013) Z-scheme water splitting using two different semiconductor photocatalysts. *ACS Catal.*, **3**, 1486–1503.
- 130 Wang, X., Liu, G., Wang, L., Chen, Z.G., Lu, G.Q., and Cheng, H.M. (2012) ZnO–CdS@Cd heterostructure for effective photocatalytic hydrogen generation. *Adv. Energy Mater.*, **2**, 42–46.
- 131 Zhou, P., Yu, J., and Jaroniec, M. (2014) All-solid-state Z-scheme photocatalytic systems. *Adv. Mater.*, **26**, 4920–4935.
- 132 Tada, H., Mitsui, T., Kiyonaga, T., Akita, T., and Tanaka, K. (2006) Solid-state Z-scheme in CdS–Au–TiO₂ three-component nanojunction system. *Nat. Mater.*, **5**, 782–786.

- 133 Yeh, T.-F., Cihlá, J., Chang, C.-Y., Cheng, C., and Teng, H. (2013) Roles of graphene oxide in photocatalytic water splitting. *Mater. Today*, **16**, 78–84.
- 134 Iwase, A., Ng, Y.H., Ishiguro, Y., Kudo, A., and Amal, R. (2011) Reduced graphene oxide as a solid-state electron mediator in Z-scheme photocatalytic water splitting under visible light. *J. Am. Chem. Soc.*, **133**, 11054–11057.
- 135 Maeda, K., Higashi, M., Lu, D., Abe, R., and Domen, K. (2010) Efficient non-sacrificial water splitting through two-step photoexcitation by visible light using a modified oxynitride as a hydrogen evolution photocatalyst. *J. Am. Chem. Soc.*, **132**, 5858–5868.
- 136 Dhanasekaran, P., Salunke, H.G., and Gupta, N.M. (2012) Visible-light-induced photosplitting of water over γ' -Fe₄N and γ' -Fe₄N/ α -Fe₂O₃ nanocatalysts. *J. Phys. Chem. C*, **116**, 12156–12164.
- 137 Abe, R., Higashi, M., and Domen, K. (2011) Overall water splitting under visible light through a two-step photoexcitation between TaON and WO₃ in the presence of an iodateiodide shuttle redox mediator. *ChemSusChem*, **4**, 228–237.
- 138 Higashi, M., Abe, R., Ishikawa, A., Takata, T., and Ohtani, B. (2008) Z-scheme overall water splitting on modified-TaON photocatalysts under visible light (500 nm). *Chem. Lett.*, **37**, 138–139.
- 139 Yun, H.J., Lee, H., Kim, N.D., Lee, D.M., Yu, S., and Yi, J. (2011) A combination of two visible-light responsive photocatalysts for achieving the Z-Scheme in the solid state. *ACS Nano*, **5**, 4084–4090.
- 140 Zeitler, K. (2009) Photoredox catalysis with visible light. *Angew. Chem. Int. Ed.*, **48**, 9785–9789.
- 141 Narayanam, J.M.R. and Stephenson, C.R.J. (2011) Visible light photoredox catalysis: applications in organic synthesis. *Chem. Soc. Rev.*, **40**, 102–113.
- 142 Lang, X.C. and Zhao, J. (2014) Heterogeneous visible light photocatalysis for selective organic transformations. *Chem. Soc. Rev.*, **43**, 473–486.
- 143 Ravelli, D., Fagnoni, M., and Albini, A. (2013) Photoorganocatalysis. What for? *Chem. Soc. Rev.*, **42**, 97–113.
- 144 Kim, G. and Choi, W. (2010) Charge-transfer surface complex of EDTA–TiO₂ and its effect on photocatalysis under visible light. *Appl. Catal. B*, **100**, 77–83.
- 145 Park, Y., Singh, N.J., Kim, K.S., Tachikawa, T., Majima, T., and Choi, W. (2009) Fullerol–Titania charge-transfer-mediated photocatalysis working under visible light. *Chem.-Eur. J.*, **15**, 10843–10850.
- 146 Higashimoto, S., Kitao, N., Yoshida, N., Sakura, T., Azuma, M., Ohue, H., and Sakata, Y. (2009) Selective photocatalytic oxidation of benzyl alcohol and its derivatives into corresponding aldehydes by molecular oxygen on titanium dioxide under visible light irradiation. *J. Catal.*, **266**, 279–285.
- 147 Lang, X.J., Ma, W.H., Zhao, Y.B., Chen, C.C., Ji, H.W., and Zhao, J.C. (2012) Visible-light-induced selective photocatalytic aerobic oxidation of amines into imines on TiO₂. *Chem.-Eur. J.*, **18**, 2624–2631.
- 148 Furukawa, S., Shishido, T., Teramura, K., and Tanaka, T. (2011) Photocatalytic oxidation of alcohols over TiO₂ covered with Nb₂O₅. *ACS Catal.*, **2**, 175–179.

- 149 Sarina, S., Zhu, H.Y., Zheng, Z.F., Bottle, S., Chang, J., Ke, X.B., Zhao, J.C., Huang, Y.N., Sutrisno, A., Willans, M., and Li, G.R. (2012) Driving selective aerobic oxidation of alkyl aromatics by sunlight on alcohol grafted metal hydroxides. *Chem. Sci.*, **3**, 2138–2146.
- 150 Tsukamoto, D., Shiraishi, Y., Sugano, Y., Ichikawa, S., Tanaka, S., and Hirai, T. (2012) Gold nanoparticles located at the interface of anatase/rutile TiO₂ particles as active plasmonic photocatalysts for aerobic oxidation. *J. Am. Chem. Soc.*, **134**, 6309–6315.
- 151 Naya, S., Inoue, A., and Tada, H. (2010) Self-assembled heterosupramolecular visible light photocatalyst consisting of gold nanoparticle-loaded titanium(IV) dioxide and surfactant. *J. Am. Chem. Soc.*, **132**, 6292–6293.
- 152 Tanaka, A., Hashimoto, K., and Kominami, H. (2011) Selective photocatalytic oxidation of aromatic alcohols to aldehydes in an aqueous suspension of gold nanoparticles supported on cerium(IV) oxide under irradiation of green light. *Chem. Commun.*, **47**, 10446–10448.
- 153 Su, F. Z., Mathew, S. C., Lipner, G., Fu, X. Z., Antonietti, M., Blechert, S. and Wang, X. C. (2010) mpg-C₃N₄-catalyzed selective oxidation of alcohols using O₂ and visible light. *J. Am. Chem. Soc.*, 2010, **132**, 16299–16301.
- 154 Zheng, Z.S. and Zhou, X.S. (2012) Metal-free oxidation of α -hydroxy ketones to 1,2-diketones catalyzed by mesoporous carbon nitride with visible light. *Chin. J. Chem.*, **30**, 1683–1686.
- 155 Möhlmann, L., Baar, M., Rieß, J., Antonietti, M., Wang, X.C., and Blechert, S. (2012) Carbon nitride-catalyzed photoredox C—C bond formation with n-aryltetrahydroisoquinolines. *Adv. Synth. Catal.*, **354**, 1909–1913.
- 156 Zhang, P.F., Wang, Y., Li, H.R., and Antonietti, M. (2012) Metal-free oxidation of sulfides by carbon nitride with visible light illumination at room temperature. *Green Chem.*, **14**, 1904–1908.
- 157 Nicewicz, D.A. and MacMillan, D.W.C. (2008) Merging photoredox catalysis with organocatalysis: the direct asymmetric alkylation of aldehydes. *Science*, **322**, 77–80.
- 158 Shih, H.-W., Vander Wal, M.N., Grange, R.L., and MacMillan, D.W.C. (2010) Enantio selective α -benzylation of aldehydes via photoredox organocatalysis. *J. Am. Chem. Soc.*, **132**, 13600–13603.
- 159 Neumann, M., Földner, S., König, B., and Zeitler, K. (2011) Metal-free, cooperative asymmetric organophotoredox catalysis with visible light. *Angew. Chem. Int. Ed.*, **50**, 951–954.
- 160 Bauer, A., Westkämper, F., Grimme, S., and Bach, T. (2005) Catalytic enantioselective reactions driven by photoinduced electron transfer. *Nature*, **436**, 1139–1140.
- 161 Müller, C., Bauer, A., and Bach, T. (2009) Light-driven enantioselective organocatalysis. *Angew. Chem. Int. Ed.*, **48**, 6640–6642.
- 162 Huo, H., Shen, X., Wang, C., Zhang, L., Röse, P., Chen, L.-A., Harms, K., Marsch, M., Hilt, G., and Meggers, E. (2014) *Nature*, **515**, 100–103.
- 163 Banerjee, S., Pillai, S.C., Falaras, P., O’Shea, K.E., Byrne, J.A., and Dionysiou, D.D. (2014) New insights into the mechanism of visible light photocatalysis. *J. Phys. Chem. Lett.*, **5**, 2543–2554.

- 164 Nosaka, Y., Nishikawa, M., and Nosaka, A.Y. (2014) Spectroscopic investigation of the mechanism of photocatalysis. *Molecules*, **19**, 18248–18267.
- 165 Walsh, A., Yan, Y., Huda, M.N., Al-Jassim, M.M., and Wei, S.-H. (2009) Band edge electronic structure of BiVO_4 : elucidating the role of the Bi s and V d orbitals. *Chem. Mater.*, **21**, 547–551.
- 166 Nazeeruddin, M.K., De Angelis, F., Fantacci, S., Selloni, A., Viscardi, G., Liska, P., Ito, S., Takeru, B., and Grätzel, M. (2005) Combined experimental and DFT–TDDFT computational study of photoelectrochemical cell ruthenium sensitizers. *J. Am. Chem. Soc.*, **127**, 16835–16847.
- 167 Nayak, P.K. and Periasamy, N. (2009) Calculation of electron affinity, ionization potential, transport gap, optical band gap and exciton binding energy of organic solids using “solvation” model and DFT. *Org. Electron.*, **10**, 1396–1400.
- 168 Chai, S., Wen, S.-H., Huang, J.-D., and Han, K.-L. (2011) Density functional theory study on electron and hole transport properties of organic pentacene derivatives with electron-withdrawing substituent. *J. Comput. Chem.*, **32**, 3218–3225.
- 169 De Angelis, F., Fantacci, S., and Selloni, A. (2008) Alignment of the dye’s molecular levels with the TiO_2 band edges in dye-sensitized solar cells: a DFT–TDDFT study. *Nanotechnology*, **19**, 424002–424008.
- 170 Wendt, S., Seitsonen, A., Kim, Y., Knapp, M., Idriss, H., and Over, H. (2002) Complex redox chemistry on the RuO_2 (100) surface: experiment and theory. *Surf. Sci.*, **505**, 137–152.
- 171 Chen, J., Zhang, H., Tomov, I.V., Wolfsberg, M., Ding, X., and Rentzepis, P.M. (2007) Transient structures and kinetics of the ferrioxalate redox reaction studied by time-resolved EXAFS, optical spectroscopy, and DFT. *J. Phys. Chem. A*, **111**, 9326–9335.
- 172 Etacheri, V., Valentin, C., Schneider, J., Bahnemann, D., and Pillai, S.C. (2015) Visible-light activation of TiO_2 photocatalysts: advances in theory and experiments. *J. Photochem. Photobiol. C Photochem. Rev.*, **25**, 1–29.
- 173 Kohn, W. and Sham, L.J. (1965) Self-consistent equations including exchange and correlation effects. *Phys. Rev.*, **140**, A1133–A1138.
- 174 Hohenberg, P. (1964) Inhomogeneous electron gas. *Phys. Rev.*, **136**, B864–B871.
- 175 Burke, K. (2012) Perspective on density functional theory. *J. Chem. Phys.*, **136**, 150901.
- 176 Moniz, S., Shevlin, S.A., Martin, D., Guo, Z., and Tang, J. (2015) Visible-light driven heterojunction photocatalysts for water splitting – a critical review. *Energy Environ. Sci.*, **8**, 731–759.
- 177 Akimov, A.V., Neukirch, A.J., and Prezhdo, O.V. (2013) Theoretical insights into photoinduced charge transfer and catalysis at oxide interfaces. *Chem. Rev.*, **113**, 4496–4565.