

1

Science and Technology of Nanomaterials: Introduction

Merin Sara Thomas^{1,2}, Sabu Thomas^{2,3,4}, and Laly A. Pothen^{2,5}

¹Mar Thoma College, Department of Chemistry, Kuttapuzha P.O., Tiruvalla, Kerala 689103, India

²Mahatma Gandhi University, International and Interuniversity Centre for Nanoscience and Nanotechnology, Priyadarsini Hills P.O., Kottayam, Kerala 686560, India

³Mahatma Gandhi University, School of Chemical Sciences, Priyadarsini Hills P.O., Kottayam, Kerala 686560, India

⁴Mahatma Gandhi University, School of Energy Materials, Priyadarsini Hills P.O., Kottayam, Kerala 686560, India

⁵CMS College Kottayam (Autonomous), Department of Chemistry, CMS College Road, Kottayam, Kerala 686001, India

1.1 Introduction

The term nanotechnology refers to the organized study of materials having at least one dimension in the nanometer range (1–100 nm). Nanomaterials are characterized by their specific optical properties, magnetic properties, electrical properties, etc. These materials are widely used in biomedical, environmental, and electrical applications because of their unique properties. The properties of nanomaterials are, however, dependent on the length scales on the order of nanometers.

Opening up a new vista of study of nanoscience in the field of physics in the year 1959, Richard Feynman, a German scientist pointed out, “There is plenty of room at the bottom” [1]. Nanoscience discusses the management of nanomaterials, systems, and devices at atomic, molecular, and macromolecular levels, whereas, nanotechnology is the bunch of techniques involved in design, synthesis, characterization, and application of structures, materials, devices, and systems by manipulating shape and size at nanometer scale. Nanotechnology is the manufacturing of tools and nanodevices by controlling the matter at the atomic level.

Nanotechnology has a wide variety of applications in various fields, such as medicine, environmental remediation, and food science. Figure 1.1 depicts different applications of nanotechnology.




Figure 1.1 Applications of nanotechnology.

1.2 Classification of Nanomaterials

Nanomaterials are classified, based on their geometry, into zero-dimensional, one-dimensional, two-dimensional, and three-dimensional nanomaterials. Figure 1.2 represents the schematic sketch for each category.

1.3 Classes of Nanomaterials

Based on their origin, nanomaterials are mainly classified into organic nanoparticles (NPs), inorganic nanoparticles, and carbon-based nanoparticles.




Figure 1.2 Scheme of (a) zero-, (b) one-, (c) two-, and (d) three-dimensional nanostructured materials with different morphologies. Source: Nikolova and Chavali [2]/MDPI/Licensed under CC 4.0.




Figure 1.3 Different types of organic nanoparticles. Source: Gessner and Neundorff [3]/MDPI/Licensed under CC 4.0.

1.3.1 Organic Nanoparticles

Organic nanoparticles are solid particles derived from organic compounds. Dendrimers, ferritin, liposomes, and micelles come under this category (Figure 1.3). The biodegradability and nontoxicity of these materials are remarkable. Organic nanoparticles are mainly used in the biomedical field for drug delivery applications.

1.3.2 Inorganic Nanoparticles

Inorganic nanoparticles are mainly of two types – metal nanoparticles and metal oxide nanoparticles. Metal nanoparticles are synthesized from metals. They can be synthesized from almost all metals, such as aluminum (Al), cadmium (Cd), cobalt (Co), copper (Cu), gold (Au), iron (Fe), lead (Pb), silver (Ag), and zinc (Zn). These are characterized by their specific properties, such as high surface area-to-volume ratio, pore size, surface charge, and surface charge density.

The applicability of metal nanoparticles can be improved by the use of metal oxide nanoparticles. Table 1.1 gives a brief idea about applications of some metallic and metal oxide nanoparticles.

1.3.3 Carbon-Based Nanoparticles

If the complete skeleton of a nanoparticle is carbon, this class can be categorized into carbon-based nanoparticles. Fullerenes, graphene, carbon nanotubes (CNTs), carbon nanofibers, carbon black, etc., come under this category. Figure 1.4 represents the schematic diagram of different carbon-based nanoparticles, and Table 1.2 gives the applications of carbon-based nanoparticles.

1.4 Properties of Nanomaterials

1.4.1 Size and Surface Area

The interaction of nanomaterials mainly depends on their size and surface area. With decrease in size of nanomaterials, the surface area-to-volume ratio of nanomaterials increases and the reactivity of the surface becomes enhanced [60]. Each and every property of nanostructures depends on their size, shape, and surface area.

Table 1.1 Applications of some metallic and metal oxide nanoparticles.

Metals	Application of metallic and metal oxide nanoparticles
Titanium dioxide (Ti)	Solar cells, food wraps, medicines, pharmaceuticals, lacquers, construction, medical devices, gas sensing, photocatalyst, agriculture, paint, food, cosmetic, sterilization, antibacterial coatings [4]
Zinc and zinc oxide (Zn)	Medical and healthcare goods, sunscreens, packaging, ultraviolet (UV)-protective materials, such as textiles [5, 6]
Aluminum (Al)	Automobile industry, aircraft, heat shielding coatings, military application, corrosion, fuel additive/propellant [7, 8]
Gold (Au)	Sensory probes, cellular imaging, electronic conductors, drug delivery, therapeutic agents, organic photovoltaics, catalysis, nanofibers, textiles [9]
Iron (Fe)	Magnetic imaging, environmental remediation, glass and ceramic industry, memory tape, resonance imaging, plastics, nanowires, coatings, textiles, alloy, and catalyst applications [10]
Silica (Si)	Drug and gene delivery, adsorbents, electronic, sensor, catalysis, remediation of the environmental pollutants, additive in rubber and plastic industry, filler, electric and thermal insulators [11, 12]
Silver (Ag)	Antimicrobial coatings, textiles, batteries, surgery, wound dressings, biomedical devices, photography, electrical devices, dental work, burns treatment [13]
Copper (Cu)	Biosensors and electrochemical sensors, plastic additives, such as antibiotic, antimicrobial, and antifungal agents, coatings, textiles, nanocomposite coating, catalyst, lubricants, inks, filler [14, 15]
Cerium (Ce)	Chemical mechanical polishing/planarization, computer chip, corrosion, solar cells, fuel oxidation catalysis, automotive exhaust treatment [16]
Manganese and its oxides (Mn)	Molecular meshing, solar cells, batteries, catalysts, optoelectronics, drug delivery ion-sieves, imaging agents, magnetic storage devices, water treatment and purification [17]
Nickel (Ni)	Fuel cells, membrane fuel cells, automotive catalytic converters, plastics, nanowires, nanofibers, textiles, coatings, conduction, magnetic properties, catalyst, batteries, printing inks [18]

Source: Attarilar et al. [19]/Frontiers Media/Licensed Under CC 4.0.

1.4.2 Mechanical Properties

Mechanical properties of different nanomaterials vary with respect to the nature of materials. Nanomaterials possess excellent mechanical properties due to the unique features of nanoparticles, such as volume, surface, and quantum effects. The addition of nanoparticles to other systems will improve the grain boundary and promote the mechanical properties of materials [61, 62]. Al Ghabban et al. [63] found that addition of 3 wt% nano-SiO₂ to concrete can enhance its compressive strength, bending strength, and splitting tensile strength. Addition of up to 0.1 wt% of nanochitosan to electrospun poly lactic acid (PLA) fibers led to an increase in tensile strength of the PLA/chitosan nanoparticles (nCHS) nanocomposite membranes. Lower concentration of nCHS in the nanocomposite gave superior tensile strength compared to the




Figure 1.4 Schematic diagram of different carbon-based nanoparticles. Source: Yuan et al. [20]/Springer Nature/Licensed under CC 4.0.

Table 1.2 Applications of carbon-based nanoparticles.

Carbon-based nanoparticles	Applications
Fullerenes	Photovoltaics [21, 22], catalysis [23, 24], biomedicine [25], rechargeable batteries [26]
Graphene	Light emitting diode [27], superconductor [28], drug carrier [29, 30], hydrogen storage materials [31], battery [32, 33]
Carbon nanotubes	Electrical emitters [34], <i>air and water filtration</i> [35, 36], <i>biomedical</i> [37–39], solar collection [40]; catalyst supports [41, 42]; and coatings [43]
Carbon nanofibers	Electrocatalytic applications [44], CO ₂ adsorption [45], batteries [46, 47], supercapacitors [48, 49], <i>biomedical</i> [50, 51], biosensors [52, 53]
Carbon black nanoparticles	Elastomer-reinforcing agent in rubber [54], inks, coatings, dyes [55], electrical conductivity agent in batteries [56, 57], UV stabilizer [58], heavy metal removals [59]

neat PLA membrane [64]. The key factors that improved the mechanical properties of the composites with such a low concentration of the filler are uniform stress distribution, minimized formation of stress-concentration centers, increased interfacial area for stress transfer from the polymer matrix to the fillers, and the decreased fiber diameter [65]. However, at higher loading, above 0.1 wt% the tensile strength seemed to be lowered. This is because of the aggregation of nCHS particles having large surface area and surface energy, which leads to the poor dispersion of nCHS in PLA matrix [66].

1.4.3 Optical and Electrical Properties

The optical properties of NPs can be utilized for the construction of optoelectronic devices. Semiconductor nanomaterials are widely used in photovoltaics and photocatalysis. The size and shape of the nanoparticles are the key factors determining the optical properties. The surface modifications also affect the optical properties of nanoparticles [67]. Size and shape of modifiers also influence the optical properties of nanoparticles. The optical properties mainly depend on the internal electronic structure and are responsible for the color of the nanoparticles. The color of nanomaterial varies with its size and is characteristic of surface plasmon resonance (SPR) that occurs by the interaction of outer electron band of nanomaterial with light wavelengths [68]. Usually, metallic nanoparticles show very high optical properties [68]. Noble metal nanoparticles show outstanding plasmonic properties. Sakhno et al. [69] reported that nanocomposites of transparent polymer matrices containing nanoparticles of noble metals are specially designed for photonics, linear and non-linear optics, laser physics, and sensing applications. They found that presence of Au and Ag NPs improved the photosensitivity of nanocomposite.

Modern electronics are based on the electrical properties of nanoparticles, such as conductivity, semiconductivity, and resistivity, and these properties are always interconnected with optical properties.

1.4.4 Magnetic Properties

Magnetic properties of nanomaterials depend on the particle size, composition of the nanostructure, and synthesis methods [70]. It is a surface-dependent property and influenced by surface roughness and surface impurity [71]. Nanoparticles of less than 35 nm show the best magnetic properties. They also have peculiar magnetic properties, such as low Curie temperature, high magnetic susceptibility, and superparamagnetism [72, 73]. Metal nanoparticles, alloys, oxides, and ferrites are some examples of nanomaterials with magnetic properties.

1.5 Characterization of Nanomaterials

The different physicochemical properties of nanostructures can be studied by various characterization techniques. Some of the instrumental tools and techniques are discussed here.

1.5.1 Surface Morphology, Surface Area, Size, and Shape of Nanoparticles

Microscopic techniques are mainly used to study the morphology of nanostructures. Transmission electron microscopy (TEM), atomic force microscopy (AFM), scanning probe microscopy, and scanning tunneling microscopy (STM) are various microscopic techniques used.

The TEM is used as a strong analytical tool for structural and chemical characterization at the nanoscale. The detailed structural analysis of nanomaterials can be obtained from TEM imaging, diffraction, and microanalytical techniques [74]. A field emission source armed with a high-intensity probe beam is a characteristic of TEMs that permit elemental analysis in samples with spatial resolution 1 nm [74]. The crystal structure imaging and structure analysis of nanomaterials with a spatial resolution of 0.045 nm can be done with the help of high-resolution transmission electron microscopy (HRTEM). The interatomic distances and crystalline defects can also be studied by HRTEM imaging.

AFM is a type of scanning probe microscope, which is used to measure morphology and mechanical properties of materials at nanoscale level. The three-dimensional analysis and visualization of nanomaterials can be achieved by AFM analysis. The applicability of AFM analysis can be extended to image biological entities, analyze material interactions, study molecular force interaction, manipulate molecules on surface, investigate material nanomechanics, and mechanically fabricate 3D nanostructures.

Dynamic light scattering (DLS) is also called photon correlation spectroscopy or quasielastic light scattering. DLS technique provides information regarding hydrodynamic size, shape, structure, aggregation state, biomolecular confirmation, size distribution, and polydispersity of molecules. The basic principle of DLS is the measurement of scattered intensity at a fixed scattering angle with time. DLS is commonly used for the characterization of colloidal suspensions or dispersions, polymer solutions, and gels.

Brunauer–Emmett–Teller (BET) analysis, as well as differential mobility analyzer, can be used for surface area measurements of nanoparticles. BET analysis gives idea about the surface area, pore volume, and pore diameter of the nanomaterials.

1.5.2 Elemental and Mineral Composition

X-ray photoelectron spectroscopy (XPS), otherwise known as electron spectroscopy for chemical analysis (ESCA), is a necessary analytical weapon for the characterization of chemical composition of variety of materials.

The crystallographic studies of nanomaterials can be done by using XRD analysis and it is a nondestructive technique. XRD is used to determine interlayer spacings, elucidate structural strains, and detect impurities. The elemental analysis can be done by using inductively coupled plasma mass spectroscopy (ICP-MS) and atomic absorption spectroscopy (AAS).

1.5.3 Structures and Bonds in Nanoparticles

The chemical bonding in nanostructures like metal–oxygen bond can be studied by using Fourier transform infrared spectroscopy (FT-IR) and XPS. Surface configuration of nanoparticles is also provided by XPS, which is used for the characterization of doped graphitic carbon nanomaterials [75]. X-ray absorption spectroscopy (XAS) can also be used to get specific qualitative information about metal/metalloid species, as well as about their quantitative distribution [76]. Raman spectroscopy can also give specific information regarding the molecular interaction among nanoparticles. But low sensitivity is a problem of this technique and this can be overcome by the use of surface-enhanced Raman spectroscopy (SERS) [77]. SERS can be used at super-low concentration, even down to single-molecule level.

1.6 Current State of Nanotechnology

Nowadays, nanoscience and nanotechnology have been found to achieve incredible interest in the academic and research field. Nanotechnology finds its application in various interdisciplinary areas of chemistry, physics, life sciences, medicine, and engineering. It was found that nanotechnology has an impact on the chemical, energy, electronics, and space industries. Nanotechnology has the potential to overcome several limitations associated with conventional technology. Nanomaterials are characterized by their surface and mechanical properties. These advantages are taken into consideration in material science.

The unique size of nanomaterials helps it to pierce into cells of animals, and thus, these materials are widely used in biology and medicine for targeted drug delivery and detection of diseases. Researchers found that the nanoparticles are capable of protecting drug from degradation because of their shield-like properties.

In industry, nanoscale materials are used in consumer products, such as cosmetics and sunscreens, fibers and textiles, dyes, and paints [78]. Electronic engineering field also finds emerging applications of nanoscale materials because of the utility of nanostructured materials as smaller, faster data storage devices [79]. Optical devices have also taken the advantage of data storage devices because that can produce images of atomic and molecular processes at surfaces [80].

1.7 Safety Issues of Nanotechnology

In spite of the wide applicability of nanomaterials, the safety of nanomaterials is still debated. The risks of nanomaterials and their products are uncertain. The alarms about the potential hazards of nanomaterials are based on their exceptional surface area, catalytic and magnetic properties, and the impact of these properties in biological systems and the environment. Due to these peculiar properties, nanomaterials are highly reactive and transformed into other forms. The transformations may occur through agglomeration, redox reactions, dissolution, exchange of surface moieties, and reactions with biomacromolecules. For example, the use of nanoparticles




Figure 1.5 Toxicity mechanism of nanoparticles mediated by reactive oxygen species (ROS) generation. Source: Sengul and Asmatulu [81]/with permission of Springer Nature.

may lead to the release of respirable particles with unusual nanostructures; the degradation of nanoproducts at the end of their life may lead to previously encapsulated nanostructured materials being released into the environment.

Researchers found that exposure to nanoparticles leads to the production of reactive oxygen species (ROS), resulting in toxicity [81]. Accumulation of iron oxide, ZnO, TiO₂ nanoparticles in lung, liver, spleen, etc., leads to oxidative stress resulting in inflammation, low cell viability, cell lysis, and disturbance of the blood coagulation system.

Figure 1.5 is the model that describes extracellular sources of ROS as exposure routes for the engineered nanoparticles. Intracellular ROS can be generated from the mitochondria, which later causes lipid peroxidation, DNA damage, and protein denaturation [81].

In food sector, nanopackaging may lead to some hazardous effects due to poor packaging. These hazardous effects depend on toxicity of the nanomaterial used, nature of packaging matrix, degree of migration, and ingestion rate of the particular food [82, 83]. Presence of some inorganic nanoparticles, such as silver nanoparticles, may also get agglomerated in various internal organs of animals [84].

1.8 Conclusion

In this chapter, we have provided a short understanding of nanoscience and nanotechnology, properties of nanomaterials, and different characterization techniques. This chapter also covers the current state of nanomaterials and their risk assessment. Nanomaterials are smart materials with a wide range of applications in the field of biology, medicine, optoelectronics, food technology, etc. But there are some risk factors also associated with this field. The safe and sustainable use of nanomaterials is desirable.

References

- 1 Feynman, R.P. (1960). There's plenty of room at the bottom. Caltech Engineering and Science, February 1960. This is a transcript of Feynman's talk given on December 29, 1959 at the Annual Meeting of the American Physical Society.
- 2 Nikolova, M.P. and Chavali, M.S. (2020). Metal oxide nanoparticles as biomedical materials. *Biomimetics* 5 (2): 27.
- 3 Gessner, I. and Neundorf, I. (2020). Nanoparticles modified with cell-penetrating peptides: conjugation mechanisms, physicochemical properties, and application in cancer diagnosis and therapy. *International Journal of Molecular Sciences* 21 (7): 2536.
- 4 Waghmode, M.S., Gunjal, A.B., Mulla, J.A. et al. (2019). Studies on the titanium dioxide nanoparticles: biosynthesis, applications and remediation. *SN Applied Sciences* 1 (4): 1–9.
- 5 Ong, C.B., Ng, L.Y., and Mohammad, A.W. (2018). A review of ZnO nanoparticles as solar photocatalysts: synthesis, mechanisms and applications. *Renewable and Sustainable Energy Reviews* 81: 536–551.
- 6 Qi, L., Xu, Z., Jiang, X. et al. (2004). Preparation and antibacterial activity of chitosan nanoparticles. *Carbohydrate Research* 339 (16): 2693–2700.
- 7 Ghorbani, H.R. (2014). A review of methods for synthesis of Al nanoparticles. *Oriental Journal of Chemistry* 30 (4): 1941–1949.
- 8 Hassanpour, P., Panahi, Y., Ebrahimi-Kalan, A. et al. (2018). Biomedical applications of aluminium oxide nanoparticles. *Micro & Nano Letters* 13 (9): 1227–1231.
- 9 Pohanka, M. (2021). Current biomedical and diagnostic applications of gold micro and nanoparticles. *Mini Reviews in Medicinal Chemistry* 21 (9): 1085–1095.
- 10 Hasany, S.F., Abdurahman, N.H., Sunarti, A.R., and Jose, R. (2013). Magnetic iron oxide nanoparticles: chemical synthesis and applications review. *Current Nanoscience* 9 (5): 561–575.
- 11 Zou, H., Wu, S., and Shen, J. (2008). Polymer/silica nanocomposites: preparation, characterization, properties, and applications. *Chemical Reviews* 108 (9): 3893–3957.
- 12 Alsaba, M.T., Al Dushaishi, M.F., and Abbas, A.K. (2020). A comprehensive review of nanoparticles applications in the oil and gas industry. *Journal of Petroleum Exploration and Production Technologies* 10 (4): 1389–1399.
- 13 Natsuki, J., Natsuki, T., and Hashimoto, Y. (2015). A review of silver nanoparticles: synthesis methods, properties and applications. *International Journal of Materials Science and Applications* 4 (5): 325–332.
- 14 Din, M.I. and Rehan, R. (2017). Synthesis, characterization, and applications of copper nanoparticles. *Analytical Letters* 50 (1): 50–62.
- 15 Rafique, M., Shaikh, A.J., Rasheed, R. et al. (2017). A review on synthesis, characterization and applications of copper nanoparticles using green method. *Nano* 12 (04): 1750043.
- 16 Dhall, A. and Self, W. (2018). Cerium oxide nanoparticles: a brief review of their synthesis methods and biomedical applications. *Antioxidants*. 7 (8): 97.

- 17 Hoseinpour, V. and Ghaemi, N. (2018). Green synthesis of manganese nanoparticles: applications and future perspective – a review. *Journal of Photochemistry and Photobiology B: Biology* 189: 234–243.
- 18 Sana, S.S., Singh, R.P., Sharma, M. et al. (2021). Biogenesis and application of nickel nanoparticles: a review. *Current Pharmaceutical Biotechnology* 22 (6): 808–822.
- 19 Attarilar, S., Yang, J., Ebrahimi, M. et al. (2020). The toxicity phenomenon and the related occurrence in metal and metal oxide nanoparticles: a brief review from the biomedical perspective. *Frontiers in Bioengineering and Biotechnology* 8: 822.
- 20 Yuan, X., Zhang, X., Sun, L. et al. (2019). Cellular toxicity and immunological effects of carbon-based nanomaterials. *Particle and Fibre Toxicology* 16 (1): 1–27.
- 21 Collavini, S. and Delgado, J.L. (2018). Fullerenes: the stars of photovoltaics. *Sustainable Energy & Fuels* 2 (11): 2480–2493.
- 22 Umeyama, T. and Imahori, H. (2019). Isomer effects of fullerene derivatives on organic photovoltaics and perovskite solar cells. *Accounts of Chemical Research* 52 (8): 2046–2055.
- 23 Vidal, S., Marco-Martínez, J., Filippone, S., and Martín, N. (2017). Fullerenes for catalysis: metallofullerenes in hydrogen transfer reactions. *Chemical Communications* 53 (35): 4842–4844.
- 24 Gopiraman, M., Saravanamoorthy, S., Ullah, S. et al. (2020). Reducing-agent-free facile preparation of Rh-nanoparticles uniformly anchored on onion-like fullerene for catalytic applications. *RSC Advances* 10 (5): 2545–2559.
- 25 Skipa, T.A. and Koltover, V.K. (2019). Fullerene trend in biomedicine: expectations and reality. *Neuroscience Research* 86 (16): 3622–3634.
- 26 Jiang, Z., Zhao, Y., Lu, X., and Xie, J. (2021). Fullerenes for rechargeable battery applications: recent developments and future perspectives. *Journal of Energy Chemistry* 55: 70–79.
- 27 Jiang, G., Tian, H., Wang, X.-F. et al. (2019). An efficient flexible graphene-based light-emitting device. *Nanoscale Advances* 1 (12): 4745–4754.
- 28 Suwandi, J.S., Toes, R.E.M., Nikolic, T., and Roep, B.O. (2015). Inducing tissue specific tolerance in autoimmune disease with tolerogenic dendritic cells. *Clinical and Experimental Rheumatology* 33: 97–103.
- 29 Trusek, A., Kijak, E., and Granicka, L. (2020). Graphene oxide as a potential drug carrier – chemical carrier activation, drug attachment and its enzymatic controlled release. *Materials Science and Engineering: C* 116: 111240.
- 30 Dastani, N., Arab, A., and Raissi, H. (2021). DFT study of Ni-doped graphene nanosheet as a drug carrier for multiple sclerosis drugs. *Computational & Theoretical Chemistry* 1196: 113114.
- 31 Masjedi-Arani, M., Ghiyasiyan-Arani, M., Amiri, O., and Salavati-Niasari, M. (2020). CdSnO₃-graphene nanocomposites: ultrasonic synthesis using glucose as capping agent and characterization for electrochemical hydrogen storage. *Ultrasonics Sonochemistry* 61: 104840.

- 32 Alhajji, E., Zhang, F., and Alshareef, H.N. (2021). Status and prospects of laser-induced graphene for battery applications. *Energy Technology* 9 (10): 2100454.
- 33 Lai, C., Gong, M., Zhou, Y. et al. (2020). Sulphur modulated Ni₃FeN supported on N/S co-doped graphene boosts rechargeable/flexible Zn-air battery performance. *Applied Catalysis B: Environmental* 274: 119086.
- 34 Al-Tabbakh, A.A. (2020). The behavior of Fowler–Nordheim plot from carbon nanotubes-based large area field emitters arrays. *Ultramicroscopy* 218: 113087.
- 35 Zarghami, S., Mohammadi, T., Sadrzadeh, M., and Van der Bruggen, B. (2020). Bio-inspired anchoring of amino-functionalized multi-wall carbon nanotubes (N-MWCNTs) onto PES membrane using polydopamine for oily wastewater treatment. *Science of the Total Environment* 711: 134951.
- 36 Haghghat, N. and Vatanpour, V. (2020). Fouling decline and retention increase of polyvinyl chloride nanofiltration membranes blended by polypyrrole functionalized multiwalled carbon nanotubes. *Materials Today Communications* 23: 100851.
- 37 Prajapati, S.K., Malaiya, A., Kesharwani, P. et al. (2020). Biomedical applications and toxicities of carbon nanotubes. *Drug and Chemical Toxicology* 45: 1–16.
- 38 Deshmukh, M.A., Jeon, J.-Y., and Ha, T.-J. (2020). Carbon nanotubes: an effective platform for biomedical electronics. *Biosensors & Bioelectronics* 150: 111919.
- 39 Negri, V., Pacheco-Torres, J., Calle, D., and López-Larrubia, P. (2020). Carbon nanotubes in biomedicine. In: *Surface-Modified Nanobiomaterials for Electrochemical and Biomedicine Applications* (ed. A.R. Puente-Santiago and D. Rodríguez-Padrón), 177–217. Springer.
- 40 Khan, D., Ali, Z., Asif, D. et al. (2021). Incorporation of carbon nanotubes in photoactive layer of organic solar cells. *Ain Shams Engineering Journal* 12 (1): 897–900.
- 41 Qin, H., Wang, Y., Wang, B. et al. (2021). Cobalt porphyrins supported on carbon nanotubes as model catalysts of metal-N₄/C sites for oxygen electrocatalysis. *Journal of Energy Chemistry* 53: 77–81.
- 42 Wang, S., Wu, T., Lin, J. et al. (2020). Iron–potassium on single-walled carbon nanotubes as efficient catalyst for CO₂ hydrogenation to heavy olefins. *ACS Catalysis* 10 (11): 6389–6401.
- 43 Deyab, M.A. and Awadallah, A.E. (2020). Advanced anticorrosive coatings based on epoxy/functionalized multiwall carbon nanotubes composites. *Progress in Organic Coatings* 139: 105423.
- 44 Wang, X., Zhang, X., Fu, G., and Tang, Y. (2021). Recent progress of electrospun porous carbon-based nanofibers for oxygen electrocatalysis. *Materials Today Energy* 22: 100850.
- 45 Li, Q., Guo, J., Xu, D. et al. (2018). Electrospun N-doped porous carbon nanofibers incorporated with NiO nanoparticles as free-standing film electrodes for high-performance supercapacitors and CO₂ capture. *Small* 14 (15): 1704203.
- 46 Zheng, J., Zhang, H., Zhao, Z., and Han, C.C. (2012). Construction of hierarchical structures by electrospinning or electrospaying. *Polymer* 53 (2): 546–554.

- 47 Xu, Y., Zhang, C., Zhou, M. et al. (2018). Highly nitrogen doped carbon nanofibers with superior rate capability and cyclability for potassium ion batteries. *Nature Communications* 9 (1): 1–11.
- 48 Levitt, A.S., Alhabeab, M., Hatter, C.B. et al. (2019). Electrospun MXene/carbon nanofibers as supercapacitor electrodes. *Journal of Materials Chemistry A* 7 (1): 269–277.
- 49 Wang, H., Niu, H., Wang, H. et al. (2021). Micro-meso porous structured carbon nanofibers with ultra-high surface area and large supercapacitor electrode capacitance. *Journal of Power Sources* 482: 228986.
- 50 Abdo, G.G., Zagho, M.M., Al Moustafa, A.E. et al. (2021). A comprehensive review summarizing the recent biomedical applications of functionalized carbon nanofibers. *Journal of Biomedical Materials Research Part B: Applied Biomaterials* 109 (11): 1893–1908.
- 51 Yadav, D., Amini, F., and Ehrmann, A. (2020). Recent advances in carbon nanofibers and their applications – a review. *European Polymer Journal* 138: 109963.
- 52 Jeong, G., Oh, J., and Jang, J. (2019). Fabrication of N-doped multidimensional carbon nanofibers for high-performance cortisol biosensors. *Biosensors & Bioelectronics* 131: 30–36.
- 53 Erden, P.E., Selvi, C.K., and Kılıç, E. (2021). A novel tyramine biosensor based on carbon nanofibers, 1-butyl-3-methylimidazolium tetrafluoroborate and gold nanoparticles. *Microchemical Journal* 170: 106729.
- 54 Poikelispää, M., Das, A., Dierkes, W., and Vuorinen, J. (2015). The effect of coupling agents on silicate-based nanofillers/carbon black dual filler systems on the properties of a natural rubber/butadiene rubber compound. *Journal of Elastomers & Plastics* 47 (8): 738–752.
- 55 Ding, X., Yu, M., Wang, Z. et al. (2019). A promising clean way to textile colouration: cotton fabric covalently-bonded with carbon black, cobalt blue, cobalt green, and iron oxide red nanoparticles. *Green Chemistry* 21 (24): 6611–6621.
- 56 Lee, D.-M., Kao, C.-W., Huang, T.-W. et al. (2016). Electrospinning of sheath-core structured chitosan/polylactide nanofibers for the removal of metal ions. *International Polymer Processing* 31 (5): 533–540.
- 57 Ha, D.-H., Islam, M.A., and Robinson, R.D. (2012). Binder-free and carbon-free nanoparticle batteries: a method for nanoparticle electrodes without polymeric binders or carbon black. *Nano Letters* 12 (10): 5122–5130.
- 58 Ammala, A., Hill, A.J., Meakin, P. et al. (2002). Degradation studies of polyolefins incorporating transparent nanoparticulate zinc oxide UV stabilizers. *Journal of Nanoparticle Research* 4 (1): 167–174.
- 59 Cheng, J., Sun, Z., Yu, Y. et al. (2019). Effects of modified carbon black nanoparticles on plant-microbe remediation of petroleum and heavy metal co-contaminated soils. *International Journal of Phytoremediation* 21 (7): 634–642.
- 60 Gattoo, M.A., Naseem, S., Arfat, M.Y. et al. (2014). Physicochemical properties of nanomaterials: implication in associated toxic manifestations. *BioMed Research International* 2014: <https://doi.org/10.1155/2014/498420>.

- 61 Zou, B., Huang, C.Z., Wang, J., and Liu, B.Q. (2006). Effect of nano-scale TiN on the mechanical properties and microstructure of Si₃N₄ based ceramic tool materials. In: *Key Engineering Materials* (ed. Z. Yuan, X. Xu, D. Zuo, et al.), 154–158. Trans Tech Publications.
- 62 Wang, X.H., Xu, C.H., Yi, M.D., and Zhang, H.F. (2011). Effects of nano-ZrO₂ on the microstructure and mechanical properties of Ti (C, N)-based cermet die materials. In: *Advanced Materials Research* (ed. Z.Y. Jiang, X.H. Liu and J. Bu), 1319–1323. Trans Tech Publications.
- 63 Al Ghabban, A., Al Zubaidi, A.B., Jafar, M., and Fakhri, Z. (2018). Effect of nano SiO₂ and nano CaCO₃ on the mechanical properties, durability and flowability of concrete. In: *IOP Conference Series: Materials Science and Engineering*, 12016. IOP Publishing.
- 64 Thomas, M.S., Pillai, P.K.S., Faria, M. et al. (2020). Polylactic acid/nano chitosan composite fibers and their morphological, physical characterization for the removal of cadmium(II) from water. *Journal of Applied Polymer Science* 137 (34): 48993.
- 65 Li, Y., Lim, C.T., and Kotaki, M. (2015). Study on structural and mechanical properties of porous PLA nanofibers electrospun by channel-based electrospinning system. *Polymer (United Kingdom)* 56: 572–580.
- 66 Augustine, R., Dominic, E.A., Reju, I. et al. (2014). Electrospun polycaprolactone membranes incorporated with ZnO nanoparticles as skin substitutes with enhanced fibroblast proliferation and wound healing. *RSC Advances* 4 (47): 24777–24785.
- 67 Saleh, T.A. (2020). Nanomaterials: classification, properties, and environmental toxicities. *Environmental Technology and Innovation* 20: 101067.
- 68 Wang, L., Hasanzadeh Kafshgari, M., and Meunier, M. (2020). Optical properties and applications of plasmonic-metal nanoparticles. *Advanced Functional Materials* 30 (51): 2005400.
- 69 Sakhno, O., Yezhov, P., Hryn, V. et al. (2020). Optical and nonlinear properties of photonic polymer nanocomposites and holographic gratings modified with noble metal nanoparticles. *Polymers (Basel)* 12 (2): 480.
- 70 Lakshmi prasanna, H.R., Angadi, V.J., Babu, B.R. et al. (2019). Effect of Pr³⁺-doping on the structural, elastic and magnetic properties of Mn-Zn ferrite nanoparticles prepared by solution combustion synthesis method. *Chemical Data Collections* 24: 100273.
- 71 Berkowitz, A.E., Kodama, R.H., Makhlof, S.A. et al. (1999). Anomalous properties of magnetic nanoparticles. *Journal of Magnetism and Magnetic Materials* 196: 591–594.
- 72 Wu, K., Su, D., Liu, J. et al. (2019). Magnetic nanoparticles in nanomedicine: a review of recent advances. *Nanotechnology* 30 (50): 502003.
- 73 Shabatina, T.I., Vernaya, O.I., Shabatin, V.P., and Melnikov, M.Y. (2020). Magnetic nanoparticles for biomedical purposes: modern trends and prospects. *Magnetochemistry* 6 (3): 30.

- 74 Smith, D.J. (2015). Characterization of nanomaterials using transmission electron microscopy. In: *Nanocharacterisation* (ed. A.I. Kirkland and S.J. Haigh), 1–29. Royal Society of Chemistry.
- 75 Susi, T., Pichler, T., and Ayala, P. (2015). X-ray photoelectron spectroscopy of graphitic carbon nanomaterials doped with heteroatoms. *Beilstein Journal of Nanotechnology* 6 (1): 177–192.
- 76 Kolahalam, L.A., Viswanath, I.V.K., Diwakar, B.S. et al. (2019). Review on nanomaterials: synthesis and applications. *Materials Today: Proceedings* 18: 2182–2190.
- 77 Zhao, X., Liu, C., Yu, J. et al. (2020). Hydrophobic multiscale cavities for high-performance and self-cleaning surface-enhanced Raman spectroscopy (SERS) sensing. *Nanophotonics* 9 (16): 4761–4773.
- 78 Stark, W.J., Stoessel, P.R., Wohlleben, W., and Hafner, A. (2015). Industrial applications of nanoparticles. *Chemical Society Reviews* 44 (16): 5793–5805.
- 79 Lyshevski, S.E. (2018). *Nano and Molecular Electronics Handbook*. CRC Press.
- 80 Jensen, T.R., Malinsky, M.D., Haynes, C.L., and Van Duyne, R.P. (2000). Nanosphere lithography: tunable localized surface plasmon resonance spectra of silver nanoparticles. *The Journal of Physical Chemistry B* 104 (45): 10549–10556.
- 81 Sengul, A.B. and Asmatulu, E. (2020). Toxicity of metal and metal oxide nanoparticles: a review. *Environmental Chemistry Letters* 18 (5): 1659–1683.
- 82 Cushen, M., Kerry, J., Morris, M. et al. (2012). Nanotechnologies in the food industry – recent developments, risks and regulation. *Trends in Food Science and Technology* 24 (1): 30–46.
- 83 Sahoo, M., Vishwakarma, S., Panigrahi, C., and Kumar, J. (2021). Nanotechnology: current applications and future scope in food. *Food Frontiers* 2 (1): 3–22.
- 84 McClements, D.J. and Xiao, H. (2017). Is nano safe in foods? Establishing the factors impacting the gastrointestinal fate and toxicity of organic and inorganic food-grade nanoparticles. *npj Science of Food* 1 (1): 1–13.

